

BERQUIST® GAP FILLER TGF 6500LVO

March 2026

Product description

BERQUIST® GAP FILLER TGF 6500LVO provides the following product characteristics:

Technology	Silicone
Appearance - Part A	Red
Appearance - Part B	White
Appearance (cured)	Pale red
Cure	Room temperature cure or heat cure
Application	Thermal management Cure in place Gap Filler (2K)
Mix Ratio by weight: Part A : Part B	1:1
Mix ratio by volume: Part A: Part B	1:1
Operating temperature, °C	-40 to 150

Features and benefits

- Thermal conductivity, 6.5, W/(m.K)
- Low volatile outgassing (LVO)
- Suited for thin bondline thickness
- Outstanding dispensing flow behavior
- Improved storage and sedimentation stability

BERQUIST® GAP FILLER TGF 6500LVO is a silicone, 2-part room temperature curable gap filler suitable for use in a wide range of electronic assembly applications. With 6.5 W/(m.K) thermal conductivity and the possibility to achieve thin bondline thickness, it provides an excellent and versatile solution to optimize heat dissipation in demanding applications. Its superior mechanical stability offers reliability and consistency over harsh operating conditions over lifetime of electronics components.

This material is an exceptional choice for use in automotive, industrial and consumer applications.

Typical applications

- Automotive control modules
- ADAS applications
- Power conversion components such as OBC, DCDC, Inverters
- Applications sensitive to siloxane outgassing
- High throughput manufacturing
- Applications where heat transfer needs to be optimized by material's thin bondline

Typical properties of uncured material

Part A properties

Viscosity, Pa.s:	
Low shear rate, 1.0 s ⁻¹ , DIN 53019	1035
Shelf-Life @ 25°C, days	180*
*shelf-life validation under investigations	

Part B properties

Viscosity, Pa.s:	
Low shear rate, 1.0 s ⁻¹ , DIN 53019	972
Shelf-Life @ 25°C, days	180*
*shelf-life validation under investigations	

Mixed properties

Bondline thickness, Internal*, µm	141
Density, ASTM D792, g/cc	3.1
Working time @ 25°C, ASTM D4473, min	172
Working time @ 40°C, ASTM D4473, min	51
*Adaptive compression speed, 0.1 MPa max stress, 25 mm diameter plate	

Typical curing performance

Cure schedule, ASTM D4473

@ 25°C, hour	8
@ 100°C, hour	0.5

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

Typical properties of cured material

Physical properties

Hardness, ASTM D2240, Shore OO	84
Siloxane content:	
ΣD4 – D6, ASTM F2466, ppm	ND**
ΣD7 – D10, ASTM F2466, ppm	<50
**ND: Not Detectable	

Electrical properties

Dielectric constant, ASTM D150	6.5
Dielectric strength, AC, ASTM D149, kV/mm	>10
Volume resistivity, DC, ASTM D257, Ω.m	>10E14

Thermal properties

Thermal conductivity, ASTM D5470, W/(m.K) >6.5

General information

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on the specifications of this product.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

Configurations available

BERQUIST® GAP FILLER TGF 6500LVO is available in the following configurations:

Cartridges, cc	50; 400; 1,200
Pail kits, gallons	6
Glass-bead configuration available, μm (mils)	none

Storage

Store product in unopened container in controlled environment, ideally between 5 to 25°C.

Optimal storage: 20°C for a 6-month shelf life in original packaging.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Shipping conditions

Short periods of time above the recommended storage temperature have not been shown to affect material's properties, negatively.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.



Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 4