

BONDERITE C-AK 187 G

Known as Novaclean 187G
July 2017

PRODUCT DESCRIPTION

BONDERITE C-AK 187 G provides the following product characteristics:

Technology	Cleaner
Product Type	Liquid alkaline cleaner
Application	Steel Strip

BONDERITE C-AK 187 G is a high alkalinity, heavy duty, dip, spray and electro-cleaner, formulated for fast efficient cleaning of steel in continuous sheet and strip plants.

It can also be used to degrease brass prior to electroplating.

BONDERITE C-AK 187 G incorporates a blend of surfactants for the rapid penetration and emulsification of a wide range of rolling oils.

Such emulsions are designed to be sufficiently unstable to allow separation of oil on standing, for subsequent effluent disposal.

The surfactant system is low foaming at ambient temperatures and negligible foam is produced at normal operating temperatures of 50°C and above.

This property enables the solution to be circulated during the build-up to operating temperatures, without excessive foam generation.

Incorporation of sequestrants prevents precipitation of hard water salts in water up to 150 ppm hardness, when the product is used at normal spray cleaning use concentration.

BONDERITE C-AK 187 G contains no silicates. Any residues left after rinsing will not inhibit subsequent pickling and plating operations.

NB: When cleaning zinc coated components prior to painting, high concentration Solutions may convert surface zinc to insoluble zinc salts which reduce subsequent phosphate treatment and paint adhesion efficiency. This may be prevented by using a low cleaner concentration and following with a sour rinse.

TECHNICAL DATA

Appearance: pale yellow , clear liquid
Specific gravity (20°C), g/cm³: 1.42

DIRECTIONS FOR USE

Preliminary Statement:

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Application:

BONDERITE C-AK 187 G is primarily intended for use in high speed strip coating lines, for the rapid removal of rolling oils and particulate matter by both spray and electro-cleaning techniques. It is also effective in removing pressing and drawing lubricants in electro-cleaning operations prior to electro-plating, or spray cleaning prior to vitreous enamelling.

Operating Parameters:

a) Soak Cleaning:

Concentration	1 to 5 % (v/v)
Temperature	50 to 80 °C
Time	2 to 10 min

b) Spray Cleaning:

Concentration	2.5 to 4 % (v/v)
Temperature	50 to 70 °C
Spray pressure	20 to 40 psi
Time	15 sec - 3 min

NB: For zinc coated steel, prior to painting, maximum concentration is 1% v/v

c) Electro-cleaning:

Concentration	5 to 10 % (v/v)
Temperature	50 to 80 °C
Current density	2 to 10 Amps/ dm ²
Time	15 sec - 5 min

Optimum operating conditions for specific applications will be advised by the Henkel Technical Representative.

Equipment:

Mild steel is suitable for the construction of tanks, pipework and other equipment. Brass, aluminium or other light alloy fittings must not be used.

Strength Determination and Control:

Titrate a 10 mL aliquot of working solution with N acid to phenolphthalein end point.

Concentration: (% v/v) = 1.03 x titration (mL N acid)
 (% w/w) = 1.46 x titration (mL N acid)

Effluent Information:

A solution of BONDERITE C-AK 187 G left to stand for up to 24 hours will separate into water and oil phases which may be wired off for disposal.

The spent aqueous phase should be adjusted with acid to a pH acceptable to the local drainage authority, before disposal.

Precautions:

BONDERITE C-AK 187 G contains caustic alkalis. Avoid contact with the skin, eyes and clothing. Causes burns.

Normal precautions for handling caustic product should be observed, including the wearing of PVC or rubber gloves, apron and face shield or goggles approved to EN 166/3F.

In case of spillage or contact with skin or clothing, drench with plenty of water. For eyes rinse with clean water and continue Irrigation for at least ten minutes, whilst obtaining medical advice.

Storage:

Recommended Storage Temperature, °C	0 to 50
Shelf-life, months (in unopened original packaging)	24

Classification:

Please refer to the corresponding **Material Safety Data Sheets** for details on:

Hazards identification
Transport information
Regulatory information

ADDITIONAL INFORMATION**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 0.0