

BONDERITE C-AK 7163 CF/4

Known as Ridoline 7163 CF/4
May 2022

PRODUCT DESCRIPTION

BONDERITE C-AK 7163 CF/4 provides the following product characteristics:

Technology	Industrial Cleaner
Product Type	Alkaline Cleaner
Application	Parts Cleaning

BONDERITE C-AK 7163 CF/4 is an alkaline, two pack, cleaner for application by spray or dip. It is especially recommended where cleaning is followed by phosphate treatment. The formulation minimises alkaline passivation of steel surfaces and ensures that phosphate coatings are smooth and even. All detergents used in this product are classed as Biodegradable. The liquid formulation eliminates any risk of airborne dust problems sometimes found with powdered cleaners.

Application Areas:

BONDERITE C-AK 7163 CF/4 is suitable for use with automatic control equipment.

BONDERITE C-AK 7163 CF/4 is suitable for mixed metal production, for example where galvanised steel, electro-deposited zinc, zinc die castings or aluminum are present along with the steel.

DIRECTIONS FOR USE

Preliminary Statement:

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Bath Make-up:

Chemicals required: BONDERITE C-AK 7163 CF/4

RIDOSOL 500CF

The normal working strength is 5 to 20 L/1,000 L for spray applications and 5.3 L/1,000 L for dip use. Add 0.5 to 1.5 L of RIDOSOL 500CF for every 10 L of BONDERITE C-AK 7163 CF/4 used.

First add the BONDERITE C-AK 7163 CF/4 to the water with the pump(s) on. Raise to operating temperature while circulating, then add RIDOSOL 500CF slowly with mixing to

the working bath.

Bath Control:

BONDERITE C-AK 7163 CF/4 control points:

Temperature	45 to 70 °C
Time spray	60 to 90 secs
Dip	90 to 600 secs
Spray pressure	1 to 2 bars (14 to 30 psi)

Concentration titration:

BONDERITE C-AK 7163 CF/4	Value
5 L/1,000	2 cm ³
10 L/1,000	4 cm ³
20 L/1,000	8 cm ³
30 L/1,000	12 cm ³

Local conditions may dictate you operate outside these parameters. Your Henkel Technical Service Representative will advise.

Measure 10 cm³ of the bath solution into a flask, add 2 to 3 drops of phenolphthalein indicator solution and titrate with 0.1N hydrochloric acid until the pink color disappears.

The number of cm³ of 0.1N hydrochloric acid added indicates the strength of the BONDERITE C-AK 7163 CF/4.

To replenish, add BONDERITE C-AK 7163 CF/4 at the rate of 2.5 L per 1,000 L of bath and RIDOSOL 500CF at the rate of 0.25 L per 1,000 L of bath for each cm³ below the desired value.

Water Rinse:

Two water rinses are desirable after BONDERITE cleaning if phosphating is to follow. Flow sufficient water into each to keep them clean.

Equipment:

Mild steel equipment is satisfactory for the cleaner and rinse stages.

BONDERITE C-AK 7163 CF/4 in a dip application, performs most satisfactorily in a tank fitted with a means of agitation. Air agitation may also be used.

Precautions:

Full information on the hazards and safe handling of the chemicals supplied are given in the corresponding Material Health&Safety Data Sheet which must be read and understood by everyone handling or using this product.

Classification:

Please refer to the corresponding **Material Safety Data Sheets** for details on:

Hazards identification
Transport information
Regulatory information

Storage:

Recommended Storage Temperature	-5 to 40°C
Shelf-life, months	24

ADDITIONAL INFORMATION**Disclaimer**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0

Henkel AG & Co. KGaA
40191 Düsseldorf, Germany
Phone: +49-211-797-0

Henkel Corporation USA
Madison Heights, MI 48071
Phone: +1-248-583-9300

Henkel (China) Co. Ltd.
201203 Shanghai, China
+86.21.2891.8000

For more information, please contact us on www.henkel.com