

## BONDERITE C-IC 144

June 2017

### PRODUCT DESCRIPTION

BONDERITE C-IC 144 provides the following product characteristics:

<b>Technology</b>	Industrial Cleaner
<b>Product Type</b>	Acid Cleaner / Pickle
<b>Application</b>	Parts Cleaning, Derusting
<b>Operating Temperature</b>	70 to 85 °C immersion process

It is composed of phosphoric acid, inhibitors, anionic and nonionic surfactants.

### Application Areas:

Cleaning and degreasing of iron, steel, copper, brass and aluminium surfaces with no major metal attack. Rust and oxides are fast dissolved. Overpickling is inhibited. BONDERITE C-IC 144 is used in industrial immersion processes.

### TECHNICAL DATA

Appearance	clear, brown liquid
Density at 20°C, DIN 51757	~1.5 g/cm <sup>3</sup>
pH-value (in a solution of 10 g/L)	~1.8

### DIRECTIONS FOR USE

#### Preliminary Statement:

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

#### Bath Make-up:

Add the required amount carefully to 700 L cold water into the circulation system.

BONDERITE C-IC 144	105 to 150 kg (70 to 100 L)
--------------------	--------------------------------

Before the start up, fill the tank with water to the working level (1,000 L).

#### Operating Data:

Temperature	70 to 85°C
Duration of treatment:	1 to 15 min depends on requirements
Iron(II)	max. 27 g/L
Free acid points	7 to 10

#### Bath Control:

BONDERITE C-IC 144 solution is controlled by the following analysis:

#### Titration of free acid:

Feed, mL	10 mL
Titrant:	1 N Sodium Hydroxide
End-Point:	pH 4.0
Indicator:	bromophenolblue

- Pipette 10 mL of bath solution into a 300 mL Erlenmeyer flask and add 50 mL deionised water.
- Add 4 to 5 drops of indicator.
- Titrate slowly with 1 N sodium hydroxide solution.
- The endpoint will be shown by a colour change from yellow to reddish (pH: 4.0).
- The added mL of 1 N sodium hydroxide is equal to the "Free Acid" points.

#### Titration of the iron(II) content:

Before titration the presence of iron(II) in the bath solution has to be checked. A dipped in test strip must turn red

Feed, mL	5 mL
Titrant:	0.1 N potassium permanganate
End point:	pink colour, 15 sec
Indicator:	25% sulfuric acid
Titration factor (TF):	g/L x mL
Iron (II) content:	max. 27 g/L

- Pipette 5 mL of bath solution into a 300 mL Erlenmeyer flask and add 50 mL deionised water.
- Add 10 mL of indicator.
- Immediately afterwards add slowly 0.1 N potassium permanganate with a burette, while swirling or stirring the sample.
- The endpoint will be shown by a colour change to permanent pink (persists for at least 15 sec).
- The added mL of 0.1 N potassium permanganate multiplied by the factor TF 1.12 is equal to iron(II) in g/L.

If the iron(II)-content exceeds the given limit, then part or all of the BONDERITE C-IC 144 bath must be replaced with fresh cleaner.

#### Replenishing:

For each missing mL for a volume of 1,000 L add:

BONDERITE C-IC 144	14.5 kg (9.6 L)
--------------------	-----------------

**Storage:**

Recommended Storage Temperature	0 to 40°C
Shelf-life, months	24
Frost-Sensitive	yes

**Classification:**

Please refer to the corresponding **Material Safety Data**

**Sheets** for details on:

- Hazards identification**
- Transport information**
- Regulatory information**

**ADDITIONAL INFORMATION****Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage:** [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 0.5