

BONDERITE C-IC 4902

Known as Deoxidizer 4902
November 2016

PRODUCT DESCRIPTION

BONDERITE C-IC 4902 provides the following product characteristics:

Technology	Metal Cleaning
Product Type	Acid Cleaner
Application	Spray and Immersion
Process Components	BONDERITE C-IC 4902 BONDERITE C-IC 4902 R

A solution of the BONDERITE C-IC 4902 removes oxides and alkali residues of former alkaline degreasing or etching processes on aluminum and its alloys.

BONDERITE C-IC 4902 is used in an immersion and spray process.

DIRECTION OF USE

Preliminary Statement:

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Bath Make-up:

- For the preparation of 1,000 L of the BONDERITE C-IC 4902 solution add to 500 L of water under stirring 5 to 30 kg or 4.5 to 27 L of BONDERITE C-IC 4902.
- After complete dissolution fill up with water to 1,000 L.

Operating Parameters:

Free Acid Points	2.5 to 15
Temperature	20 to 55 °C
Time	3 sec to 10 min

Process Steps:

1. Clean/ Pickle
2. Rinse
3. Deoxidize with BONDERITE C-IC 4902
4. Rinse
5. Chromate, Anodize
6. Rinse
7. Rinse with DI-water
8. Dry

Bath Control:

BONDERITE C-IC 4902 bath is controlled by a titration of the free acid-points.

Titration

- Pipette 10 mL sample of the BONDERITE C-IC 4902 bath into a flask and dilute with 50 mL of distilled water.
- Add 4 to 5 drops of indicator 4.5 (Mortimer).
- Titrate against 0.1 N caustic solution until the color changes from red to turquoise.
- Record the number of mL of 0.1 N caustic solution used as free acid-points.

Bath Replenishing

The bath should be kept within 2.5 to 15 free acid-points.

Add 2 kg or 1.8 L of BONDERITE C-IC 4902 per 1,000 L of the bath for each free acid-point lacking or 1.9 kg or 1.7 L of BONDERITE C-IC 4902 R.

BONDERITE C-IC 4902 R is preferably used in plant with low drag-out and/or high production rates.

Remarks:

The tank material containing BONDERITE C-IC 4902 should be made out of rigid PVC (free of plasticizer), PP or austenitic steel (type 1.4571).

Spraying systems, pumps and heat exchangers have to be made out of stainless steel (type 1.4571).

Plant devices likely to get in contact with the concentrate of BONDERITE C-IC 4902 should be made of rigid PVC, PP or another plastic resistant against fluorides.

BONDERITE C-IC 4902 bath as well as its rinsing solutions are not to be discharged into the public sewage system without prior detoxification and neutralization.

Particular Cautions:

BONDERITE C-IC 4902 contains sulphuric acid and fluorides.

Wear:

- Eye goggles
 - Rubber gloves
 - Acid resistant wear
- Avoid contact with skin.
Provide air circulation.

Equipment:

Pipette, 10 mL
Erlenmeyer flask, 300 mL
Graduated cylinder, 50 mL content
Burette, 25 mL
DI-water
Indicator 4.5 (Mortimer)
Caustic solution, 0.1 N

Storage

Process Component	Recommended Storage Temperature, °C	Shelf life, months (in unopened original packaging)
BONDERITE C-IC 4902	-9.9 to 40	36
BONDERITE C-IC 4902 R	-9.9 to 40	36

Classification

Please refer to the corresponding **Material Safety Data**

Sheets for details on:

- Hazards identification**
- Transport information**
- Regulatory information**

ADDITIONAL INFORMATION**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0