

Technical Data Sheet

BONDERITE L-CA CG 708 ACHESON

Known as Deltacast CG-708 September 2016

PRODUCT DESCRIPTION

BONDERITE L-CA CG 708 ACHESON provides the following product characteristics:

Technology	Lubricant
Product Type	Insulating coating
Application	Gravity and low pressure die casting

BONDERITE L-CA CG 708 ACHESON is a ready for use coarse particle size, water based die dressing for use in gravity and low pressure die casting.

BONDERITE L-CA CG 708 ACHESON is one of a series of insulating coatings, which have been developed to provide a range of controlled chilling rates; BONDERITE L-CA CG 708 ACHESON is a fairly high insulating product. It provides a tenacious long lasting coating which prevents too rapid chilling of the molten metal to facilitate the production of high quality castings.

BONDERITE L-CA CG 708 ACHESON is particularly suitable for application to areas of the mould where a very low cooling rate and/or high metalflow speeds are required.

Application

BONDERITE L-CA CG 708 ACHESON should be applied to die surfaces thoroughly cleaned of dirt, oil, grease and previous coatings. Light sandblasting is ideal, but wire brushing may be sufficient to free the surface of contamination.

Recommended is application of BONDERITE L-CA CG 708 ACHESON on top of primer coating BONDERITE L-CA CG 515 ACHESON.

To achieve uniform, long-lasting coatings, the material should be spray applied to die surfaces pre-heated between 160 to 200 °C. For brush application the surfaces to be treated should be pre-heated between 120 to 140 °C.

Several thinner coatings, dried between each application, are preferred over one heavy coating. Coatings can be touched up at normal die working temperatures.

TECHNICAL DATA

(as supplied):	
Appearance	clear, brown liquid
Coating insulation	high
Pigment	blend of refractory materials
Carrier	water
Diluent	ready for use
Solids content, %	19

DIRECTION OF USE

Preliminary Statement

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Dilution

BONDERITE L-CA CG 708 ACHESON is a ready for use product and should not be diluted before application by spray or brush.

On storage a sediment may form in the container. The concentrate should therefore be homogenised before use. Agitation may be sufficient but stirring is preferred.

Storage

Store BONDERITE L-CA CG 708 ACHESON in a cool place, but do not allow it to freeze. Product should not be used once frozen.

Always tightly reseal the container to avoid contamination.

Shelf Life

- 6 months from date of qualification under original seal.

Classification

Please refer to the corresponding **Material Safety Data Sheets** for details on:

Hazards identification Transport information Regulatory information



ADDITIONAL INFORMATION

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any

other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the

following disclaimer is applicable: The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out

your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any Any habitity in respect of the information in the resinical part of the concerned product is other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.2