

BONDERITE L-MR 46-81

Known as Multan 46-81
September 2016

PRODUCT DESCRIPTION

BONDERITE L-MR 46-81 provides the following product characteristics:

Technology	Lubricants
Product Type	Synthetic Metal Working Fluid
Application	Mineral oil free Metal Working Fluid for Grinding

BONDERITE L-MR 46-81 is a water soluble synthetic grinding fluid. BONDERITE L-MR 46-81 is a mineral oil-free general purpose full synthetic coolant suitable in a wide range of grinding operations and water hardness (5 to 60° dH). Due to the selection of raw materials, BONDERITE L-MR 46-81 is resistant against bacteria growth. The formulation of BONDERITE L-MR 46-81 provides good foam control, corrosion protection properties and grit settling characteristics. BONDERITE L-MR 46-81 complies with the German TRGS 611 (Technical Rule for Hazardous Substances 611).

Application Areas

BONDERITE L-MR 46-81 is mainly used for surface grinding or similar operations where transparency together with excellent foam control are of prime importance. BONDERITE L-MR 46-81 is preferably used for steel and cast iron and provides very good corrosion protection. Solutions made from BONDERITE L-MR 46-81 are clear and can be used with confidence in high pressure applications.

TECHNICAL DATA

(as supplied):

Concentrate:

Density, 20°C, g/cm ³ DIN 51757	~1.15
Viscosity, (20°C), mm ² /s DIN 53211	~57
Flashpoint, °C DIN ISO 2592	>100

Solution:

Appearance	clear colourless
pH	~9.3

Corrosion protection properties:

according to DIN 51360/2	0/0 at 3 %
--------------------------	------------

DIRECTION OF USE

Preliminary Statement

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Concentration

Use 3 - 4 % concentrate depending on the corrosion protection properties required by the material to be grinded.

Control of the emulsion

Refractometer:

The reading in °Brix multiplied by the product factor 1.4 is equivalent to the concentration in percent.

Titration:

100 mL of the emulsion are titrated down to pH 5.5 using 0.5 N HCl and an electronic pH-meter. The consumption of acid in mL multiplied by the product factor 0.16 is equivalent to the concentration in percent.

Storage

Temperature, °C +5 to +40

Classification

Please refer to the corresponding **Material Safety Data Sheets** for details on:

Hazards identification
Transport information
Regulatory information

ADDITIONAL INFORMATION**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference **N/A**