

BONDERITE® S-MA 5000 AERO

January 2023

PRODUCT DESCRIPTION

BONDERITE® S-MA 5000 AERO provides the following product characteristics:

Technology	Surface Treatment
Product Type	2-K maskant VOC Free
Appearance - Part A	Light green viscous liquid
Appearance - Part B	Yellow to brown viscous liquid
Mix Ratio by volume: Part A: Part B	1 : 1
Application Method	Spray
Application	Surface treatment process, Chemical milling

BONDERITE® S-MA 5000 AERO is a two-part, 100% solid 2-K maskant polyurethane based material formulated to provide an air curing, hand peelable coating. When applied, this material is designed to provide a strong protection to the metal surfaces during chemical processing.

PRODUCT BENEFITS

- 100% solid maskant
- VOC free
- Rapidly cure, allowing the user to process coated parts much faster than with conventional maskants
- One single application to provide a coating of 300 to 350 µm
- Easily applied using a 1:1 mixing ratio equipment
- Mixing at the nozzle simplifies the cleaning operations of the equipment
- No stoppage period or maintenance needed

GENERAL INFORMATION

Please consult the Safety Data Sheet (SDS) for safe handling information of this product.

DIRECTIONS FOR USE

Application

- BONDERITE® S-MA 5000 AERO is intended for use in chemical milling processes for both Aluminum and Titanium alloys.

Materials

- BONDERITE® S-MA 5000 AERO Part A
- BONDERITE® S-MA 5000 AERO Part B

Recommended Mix Ratios

1. BONDERITE® S-MA 5000 AERO part A and part B are ready to use products.
2. It is strongly recommended to mix Part A well before use.
3. Constantly stir BONDERITE® S-MA 5000 AERO during the maskant application.
4. Mix ratio (Part A: Part B) by volume is 1:1.

SURFACE TREATMENT PROCESS USING BONDERITE® S-MA 5000 AERO spray application

Surface Pre-Treatment Process

The surface pre-treatment can be operated within a two or three step chemical process.

1. The two-step process consists of an alkaline cleaning and acidic deoxidizing
2. The three-step process consists of an alkaline etching used between cleaning and deoxidizing

The adhesion of the coating depends on the type of alloys and pre-treatment used.

Cleaning

- All surfaces treated should be clean, dry and free from any contaminants that will affect adhesion.

Water Rinsing

- After cleaning, the metal must be thoroughly rinsed with water. The rinse should flow continuously at a rate which will keep it clean and free from scum and other contamination.

Alkaline Etching (Optional)

- If the aluminum to be treated has corrosive products or heavy oxides on the surface, it should be conditioned by installing two additional steps between post cleaner rinse and deoxidizing steps. The first additional step involves an alkaline etching with an etchant chemical and second step is an additional cold-water rinse.

Deoxidizing

- This step should produce a surface that is fully reactive, free from all surface oxide residue. The product must have high oxidizing power to bleach the surface by removing the dirt caused by alloying elements (i.e., copper, silicon, magnesium, etc).



Spray Application

1. BONDERITE® S-MA 5000 AERO can be applied with 1:1 spraying equipment. Henkel can present the detailed specifications, on request, for the spray gun type

A recommended sample equipment set up is shown below

- Dosing spray unit - GRACO REACTOR EXP 2
- Spray gun- GlasCraft PROBLER P2 Elite
- Mixing Chamber - Graco GC2500
- Nozzle 0.023" / 50°
- Inlet GRACO GC2512

1. For an uniform BONDERITE® S-MA 5000 AERO coat, hold the spray gun approximately 300 to 400 mm from the substrate, moving the gun parallel and at right angles to the substrate surface.
2. Use uniform straight strokes.

Recommended Spray Mix Ratios

- Mix ratio (Part A: Part B) by volume is 1:1.

Spraying Temperature

- Part A: 65±5°C
- Part B: 70±5°C

Spraying Pressure

- 140 to 180 bar

Advised film thickness

- 300±50 µm

Material

Material needed to coat 1m² / 300µm (without overspray)

- 0.3 kg (part A + part B)

After Treatment Process

Tack-free time, seconds	≥10
Handling time, minutes	≥5 to 10
Manual and laser scribing can be used on the applied coating:	
Minimum time prior to peeling, hours	4
Minimum time prior to scribing, hours	18

STORAGE AND HANDLING

Storage

Store in original, tightly covered containers in clean, dry areas. Storage information may be indicated on the product container labeling.

Storage below 5°C or above 35°C for the Part A and Part B can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Conversions

(°C x 1.8) + 32 = °F

L / 3,785 = gallons

mm / 25.4 = inches

1 bar = 14.5 Psi

dm² / L / 9,290 * 3,785 = ft² / gal

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 3