

CM 11

»CERAMIC«

Universal thin-bed adhesive mortar



CHARACTERISTICS

- For indoor use
- For earthenware and stoneware tiles
- For dry and wet rooms
- For tiles up to 40x40cm



SCOPE OF USE

Ceresit CM 11 adhesive mortar is designed for laying ceramic (glazed, terracotta) and natural stone tiles (colour-fast) on dimensionally stable substrates such as: concrete, cement screeds, cement or cement and lime plasters. Suitable for using indoors and outdoors.

The Ceresit CM 11 mortar can also be applied on deformable substrates such as plasterboards, wood chip-boards or heated floors after adding elastic emulsion Ceresit CC 83, which improves the technical parameters of the mortar. Alternatively, Ceresit CM 12 PLUS, CM 16 mortar can be used for such applications. For other types of tiles and other substrates, higher loads and deformable substrates like terraces and balconies, heated floors and plasterboards - suitable Ceresit mortars and adhesives are recommended.

For laying natural stone tiles that are not color-fast, Ceresit CM 14 White Marble & Mosaic mortar shall be used.

SUBSTRATE PREPARATION

Ceresit CM 11 adhesive mortar can be applied on even, load-bearing and compact substrates, free of any substances that reduce adherence (such as: grease, bitumen, dust):

indoors and outdoors:

- concrete (at least 3 months old)



- cement screeds (humidity ≤ 2%) and plasters, cement and lime plasters (at least 28 days old)
- **indoors:**
- anhydrite (residual moisture below 0.5%) and gypsum (residual moisture below 1%) substrates - mechanically roughened, freed from dust and primed with CT 17,
- aerated concrete - freed from dust and primed with CT 17.

Substrates must not be wet. Any existing dirt, loose layers and paint coating with low strength shall be mechanically removed. Absorbent substrates shall be primed with Ceresit CT 17 and left to dry for at least 2 hours. Surface unevenness of up to 5 mm can be filled on the previous day with the same CM 11 mortar. In the case of bigger unevenness and dents - Ceresit products from the CN group shall be used on floors and Ceresit CT 29 filler on walls.

APPLICATION

Pour the content of the package to a precisely

CERESIT_CM11 COMFORT_TDS_11_2023



Henkel AG & Co. KGaA Deutschland
Henkelstraße 67 · 40191 Düsseldorf
Internet: www.ceresit.com
E-mail: ceresit.com@henkel.com

Quality for Professionals

measured amount of clean, water or to the water solution of CC 83 emulsion (2 parts of CC 83 mixed with 1 part of water) * and stir with a drill with a mixer until it forms a homogeneous mass, free of lumps. Leave for 5 min. and then stir the mixture again. If necessary - add a small amount of water and stir once more. Spread the mortar onto the substrate with a suitable notched trowel. For indoor wall application, the mortar coverage on the tile backside should be minimum 65%. Tiles must not be soaked in water! Tiles should be laid in during the recommended time of the adhesive mortar. Do not lay tiles butt jointed! Fresh stains from the mortar can be rinsed with water, hardened stains must be removed mechanically. Grouting can be done not earlier than after 24 hours using Ceresit materials from the CE group. Expansion joints between tiles, joints at corners, in places where floor meets walls and around sanitary equipment shall be filled with Ceresit CS 25 MicroProtect silicone.

PLEASE NOTE

- ▶ Works should be carried out in dry conditions, with the air and ground temperature from +5 °C to +25 °C.
- ▶ CM 11 contains cement and after mixing with water produces an alkaline solution. Therefore, protect eyes and skin. In the case of eye contact, rinse eyes thoroughly with water and consult a doctor.
- ▶ For grouting, Ceresit CE 40 aquastatic grout is recommended. On substrates exposed to chemical aggression or mechanical impact (terraces, balconies, traffic areas) Ceresit CE 43 Grand'Elit grout shall be used.
- ▶ Dirt- and water-repellent silicone impregnation agent Ceresit CT 10 shall be used for additional protection of joints and ceramic cladding against staining.
- ▶ In the case of laying tiles made of stone that is prone to color changes, sample tests must necessarily be carried out in order to check whether the mortar causes no fading of the tiles. With the publication of this data sheet, any previous sheets become invalid.

OTHER INFORMATION

Should you need support or advice, please consult our advisory service for architects and craftsmen on the

contact information you will find on **the local Ceresit website**.

Apart from the information given here it is also important to observe the relevant guidelines, regulations and common standards of various organizations and trade associations. The afore mentioned characteristics are based on practical experience and applied testing. Confirmed

properties and possible uses which go beyond those listed in this information sheet require our written confirmation. All data given was obtained at an ambient and material temperature of +23° C and 50 % relative air humidity unless specified otherwise. Please note that under other climatic conditions hardening can be accelerated or delayed and that the product itself is subject to local conditions such as amount of water and hardening. A product from another production site may differ.

The information contained herein, particularly recommendations for the handling and use of our products, is based on our professional experience. As materials and conditions may vary with each intended application, and thus are beyond our sphere of influence, we strongly recommend that in each case sufficient tests are conducted to check the suitability of our products for their intended use. Legal liability cannot be accepted on the basis of the contents of this data sheet or any verbal advice given, unless there is a case of willful misconduct or gross negligence on our part or unless there is a case of personal injury or death or a case of liability under the Product Liability Act.

This technical data sheet supersedes all previous editions relevant to this product. Please be aware that this Technical Data Sheet only relates to a product manufactured in the specific relevant production site.

TECHNICAL DATA

Base:	mixture of cements with mineral fillers and modifiers	
Bulk density:	approx. 1.45 kg/dm ³	
Mixing ratio:		
packaging size (kg)	water amount (l)	water amount [I] + CC 83 addition [II]
5	Approx. 1.1	0.4 l of water + 0.7 l CC 83
15	Approx. 3.3	1.1 l of water + 2.2 l CC 83
25	Approx. 5.5	2 l of water + 3.5 l CC 83
27.5	Approx. 6	2 l of water + 4 l CC 83
30	Approx. 6.6	2.3 l of water + 4.3 l CC 83
Application temperature:	from +5 °C to +25 °C	
Initial maturing time:	approx. 5 min.	
Pot life:	up to 2 hours (90 min)*	
Open time (according to the EN 12004 standard):	adherence > 0.5 MPa	
Creep (according to the EN 12004 standard):	< 0.5 mm	
Grouting:	after 24 hours	



Henkel AG & Co. KGaA Deutschland
 Henkelstraße 67 · 40191 Düsseldorf
 Internet: www.ceresit.com
 E-mail: ceresit.com@henkel.com

Quality for Professionals

Adhesive tension strength (according to the EN 12004 standard):

- initial: > 0.5 MPa,
- after soaking in water: > 0.5 MPa,
- after thermal maturing: > 0.5 MPa,
- after freezing and defrosting cycles: > 0.5 MPa

Temperature resistance: from -30 °C to +70 °C

Reaction to fire: A1/A1_{fl}


Approximate consumption (for even substrates; consumption can vary depending on the evenness on the substrate and the type of tiles):

tile size	notch depth	amount of CM 11 PLUS [kg/m ²]	amount of CC 83* [l/m ²]
up to 10 cm	4 mm	2.0	0.4
up to 15 cm	6 mm	2.7	0.52
up to 25 cm	8 mm	3.4	0.65
up to 30 cm	10 mm	4.2	0.78

* with the addition of CC 83

Shelf life: Up to 12 months from the production date, if stored on pallets, in dry conditions, in original and undamaged packages.

The product is compliant with the EN 12004:2008 standard.

	Reaction to fire	A1
1487	Release of dangerous substances	see MSDS
Henkel Polska Sp. z o.o.	Bond strength, as:	
02-672 Warszawa, ul. Domaniewska	Initial tensile adhesion strength	≥ 0.5 N/mm ²
41	Durability, for:	
13	Tensile adhesion strength after water immersion	≥ 0.5 N/mm ²
00007	Tensile adhesion strength after heat ageing	≥ 0.5 N/mm ²
EN 12004:2007+A1:2012 C1 T	Tensile adhesion strength after Freeze-thaw cycles	≥ 0.5 N/mm ²
Normal setting cementitious adhesive with reduced slip	Open time: tensile adhesion strength after no less than 20 min	≥ 0.5 N/mm ²
		After at least 20 minutes
	Slip	≤ 0.5 mm



Henkel AG & Co. KGaA Deutschland
Henkelstraße 67 · 40191 Düsseldorf
Internet: www.ceresit.com
E-mail: ceresit.com@henkel.com

Quality for Professionals