

CN 69

NIVEL SUPER

Floor Levelling Compound

Self-levelling compound for medium traffic loads in 2 to 10 mm layer thickness for indoor use

CHARACTERISTICS

- ▶ reinforced with fibres
- ▶ smooth surface
- ▶ resistant to concentrated loads
- ▶ pumpable
- ▶ suitable for heated floors
- ▶ indoor

SCOPE OF USE

Self-levelling compound for producing norm-conforming substrates before covering them with final floor covering materials.

Ceresit CN 69 is suitable for concrete, cement-sand and other mineral bases to create smooth surface ready to receive textile, lamella, PVC, lino coverings as well as ceramic tiles. Also suitable for heated floors. Ceresit CN 69 is recommended for dry indoor areas.

SUBSTRATE PREPARATION

Substrates should comply with the requirements of ATV DIN 18 365 "Flooring work", ATV DIN 18 356 "Wood flooring work", BS CP 8204 & 8201 or comparable national standards.

In particular, they must be clean, sound, dry and free of cracks and substances which may impair adhesion. The following maximum permissible residual moisture contents must always be observed (indicated in CM-% measured with a Calcium-Carbide device):

Type of screed	Resilient and textile floor coverings, parquet and wood flooring, laminate flooring	
	heated	unheated
Cement screed	1.8 %	2.0 %
Calcium sulfate screed	0.3 %	0.5 %

- The ingress of moisture into the floor structure must always be prevented by suitable measures (e.g. water-proofing membranes, barrier primers). This applies in particular to composite structures and concrete floors.
- The ingress of moisture into the floor structure must always be prevented by suitable measures (e.g. water-proofing membranes, barrier primers). This applies in particular to composite structures and concrete floors.



CERESIT_CN69_TDS_1_0420

- In the case of cementitious substrates, any laitance must be removed mechanically. Always grind calcium sulfate screeds and vacuum off the dust.
- Dense, smooth surfaces like ceramic tiles and slabs must be carefully cleaned and roughened. Before applying the levelling compound, pretreat the surface with the recommended Ceresit or primer.
- Best possible indoor air quality after floor installation work requires conformity to the standard working conditions as well as completely dry substrates, primers and levelling compounds.

APPLICATION

Mix Ceresit CN 69 with clean, clear water (amount: see Technical Data). Stir with an electric drill and mixer attachment at approx. 600 rpm for about 2 minutes until the mixture is completely free of lumps. Stir twice with 2 – 3 min interval. Pour the levelling compound on the floor in the required layer thickness and spread it with a broom, smoothing trowel or squeegee. Afterwards use a spiked roller to release any entrapped air. If mixed in batches, apply the batches immediately wet in wet. Ceresit CN 69 can be applied with suitable machines. Please follow the machine manufacturer's instructions.

PLEASE NOTE


- Polymer-modified cement/gypsum combination that sets off an alkaline reaction with water.
- Only carry out floor installation work if the floor temperature is above 15 °C, air temperature above 18 °C and relative humidity below 75 %.
- Wait until the applied product is completely dry before continuing with the next steps. For this purpose, ensure favorable climatic conditions (recommended: 50 % rel. humidity, 20 °C) and adequate air circulation.
- Protect the freshly applied levelling compound from direct sunlight and draughts.
- Do not mix the product with other floor levelling compounds.
- Do not use outdoors or in areas directly or indirectly exposed to moisture. If in doubt, use suitable moisture barriers.

The risk of medium- or long-term release of appreciable concentrations of volatile organic substances (VOC) into the ambient air is negligible. Nevertheless, ensure good ventilation during and after application and drying. Avoid eating, drinking or smoking while processing this product. Strongly alkaline reaction with moisture, so protect skin and eyes. After contact wash immediately with plenty of water. After eye contact also seek medical advice. The risk of medium- or long-term release of appreciable concentrations of volatile organic substances (VOC) into the ambient air is negligible. Nevertheless, ensure good ventilation during and after application and drying. Avoid eating, drinking or smoking while processing this product. Strongly alkaline reaction with moisture, so protect skin and eyes. After contact wash immediately with plenty of water. After eye contact also seek medical advice.

Apart from the information given here it is also important to observe the relevant guidelines and regulations of various organizations and trade associations as well as the respective standards of the German Standards Institute (DIN). The aforementioned characteristics are based on practical experience and applied testing. Warranted properties and possible uses which go beyond those warranted in this information sheet require our written confirmation. All data given was obtained at an ambient and material temperature of +23 °C and 50 % relative air humidity unless specified otherwise. Please note that under other climatic conditions hardening can be accelerated or delayed.

The information contained herein, particularly recommendations for the handling and use of our products, is based on our professional experience. As materials and conditions may vary with each intended application, and thus are beyond our sphere of influence, we strongly recommend that in each case sufficient tests are conducted to check the suitability of our products for their intended use. Legal liability cannot be accepted on the basis of the contents of this data sheet or any verbal advice given, unless there is a case of wilful misconduct or gross negligence on our part. This technical data sheet supersedes all previous editions relevant to this product.

Hazard notes/Safety advices/Dangerous goods classification/waste disposal advices: See Material Safety Data Sheet.

	
1803 Henkel Polska Operations Spółka z o.o. 02-672 Warszawa, ul. Domaniewska 41 10 Ceresit CN 69 00342 EN 13813: 2002 CT-C25-F7 Cement based levelling compound for indoor use	
Reaction to fire	A1 _{fl}
Release of corrosive substances	CT
Compressive strength	C35
Flexural strength	F7

DISPOSAL

Do not allow product to reach sewage system or any water course. Do not allow to penetrate the ground/soil. Only recycle totally empty packages. Dispose of hardened product residues as industrial waste similar to household waste or in the container for commercial/construction site waste. Dispose of unhardened product residues as hazardous waste. European waste code number (EWC): 17 01 01.

PACKAGING

Bags of 25 kg.

TECHNICAL DATA

Composition:	Polymer modified cement/ gypsum combination with quartz sand and selected additives
Supplied:	as grey powder
Water ratio:	5.5 – 6.0 l/25 kg
Consumption:	approx. 1.3 kg/m ² /mm
Pot life:	max. 40 min
Ready for foot traffic:	in 12 hours
Ready for covering:	
layer thickness up to 5 mm:	in 48 hours
layer thickness 5 – 10 mm:	in 72 hours
Shelf life:	approx. 9 months if stored tightly closed in a cool and dry place. Use up opened sacks as soon as possible.

The above times are based on normal climatic conditions (20 °C/ 60 % rel. air humidity). Other climatic conditions can cause a lengthening or shortening of cure and drying times.



Henkel CEE
Erdbergstrasse 29
1030 Vienna
www.ceresit.com

Quality for Professionals