

CR 60



RENOVATION RENDERING COAT

Coating for renovation of historical buildings

CHARACTERISTICS

- ▶ Excellent adhesion
- ▶ Hydrophilic
- ▶ For indoor and outdoor use
- ▶ Increases the adhesion of renovation renders
- ▶ Application also on damp and highly salt-contaminated walls
- ▶ Suitable for manual and machine application
- ▶ Complies with WTA Code of Practice*

SCOPE OF USE

Ceresit CR 60 can be used as rough cast before application of restoration renders system on damp and salt-containing brick or concrete interior and exterior walls and foundations. Recommended to be used on historical and other buildings subject to renovation of damp and salt contaminated walls. Product is a part of Ceresit Restore restoration render system.

LAYER SELECTION

Before commencing work related to the application of the restoration render system, it is highly recommended to determine the degree of salinity of the substrate, which determines the layout and thickness of individual layers.

Ceresit Restore- restoration render system		
Degree of salinity acc. WTA	Layer arrangement	Layer thickness in mm
Low	CR 60	≤ 5
	CR 62	≥ 20
Medium	CR 60	≤ 5
	CR 61	10÷20
High	CR 62	10÷20
	CR 60	≤ 5
	CR 61	≥ 10
	CR 62	≥ 15

SUBSTRATE PREPARATION

Ceresit CR 60 adheres to all solid, load-bearing, clean, dry and damp substrates, free of substances that may impair adhesion. The surface must be rough and porous to ensure good adhesion. Existing coats and old, damaged renders must be completely removed up to a height of at least 80 cm beyond the damage zone (visible area of moisture



CERESIT_C_CR60_TDS_1_0923

penetration and salt deposition) down to the structurally sound masonry and let it dry. Replace any missing or damage bricks. Rake out loose mortar joints to a depth of approx. 20 mm and then fill with Ceresit CR 61 render. Traces of salt efflorescence should be removed with steel brushes.

APPLICATION

Pour the material into a pot with measured amount of approx. 5,5-5,6 l clean, cool water and mix with a low speed mixer until a homogeneous mass without lumps is obtained. After stirring leave material for 5 minutes maturing time and stir briefly again. The render prepared in this way should be used within approx. 2 hours. Ceresit CR 60 can also be prepared and applied with standard rendering machine. Pre-wet substrate until the surface is no longer absorbent and appears to be slightly damp. Apply mixed mortar in net-shape up to 5 mm thickness with a surface coverage of approx. 50% of the full surface area. The mortar can be applied by trowel, broom or mortar spray gun (manual render sprayer). The drying time before application of further coat of Ceresit CR 61 restoration render is approx. 24h. Ensure good ventilation during and after application and drying for indoor application and protect from drying out too quickly and from weather conditions like driving rain and frost for external application.

PLEASE NOTE

Refer in particular to the recommendations of the analysis of old render and renovation guidelines.

Fresh residues can be removed with water, hardened material can only be removed mechanically.

Use Ceresit CR 60 only in dry conditions and at temperatures of +5°C to +30°C and below 80% relative humidity. Do not mix with other materials, additives or binders. Do not use on gypsum-based substrates or cover with gypsum-based products. All data given was obtained at an ambient and material temperature of +20°C and 65% relative humidity unless specified otherwise. Please note that under other climatic conditions hardening can be accelerated or delayed. Ceresit CR 60 contains cement and shows a strongly alkaline reaction with water. Therefore protect skin and eyes. If contact occurs, rinse thoroughly with plenty of water. In case of contact with eyes, obtain medical advice.

Chromium VI content - below 2 ppm during the shelf life of the product.

Keep out of reach of children. For professional users. Hazard notes/Safety advices/ Dangerous goods classification/waste disposal advices: See Material Safety Data Sheet on mymysds.henkel.com

STORAGE

Up to 12 months since the production date when stored in cool conditions and in original undamaged packages.

PACKAGING

25 kg Paper bag with PE inlay.


Apart from the information given here it is also important to observe the relevant guidelines and regulations of various organisations and trade associations as well as the respective standards of the German Standards Institute (DIN). The aforementioned characteristics are based on practical experience and applied testing. Warranted properties and possible uses which go beyond those warranted in this information sheet require our written confirmation. All data given was obtained at an ambient and material temperature of +20 °C and 65% relative air humidity unless specified otherwise. Please note that under other climatic conditions hardening can be accelerated or delayed.

The information contained herein, particularly recommendations for the handling and use of our products, is based on our professional experience. As materials and conditions may vary with each intended application, and thus are beyond our sphere of influence, we strongly recommend that in each case sufficient tests are conducted to check the suitability of our products for their intended use. Legal liability cannot be accepted on the basis of the contents of this data sheet or any verbal advice given, unless there is a case of wilful misconduct or gross negligence on our part. This technical data sheet supersedes all previous editions relevant to this product.

TECHNICAL DATA

Material base:	mineral, hydraulic-setting premixed dry mortar
Colour:	cement grey
Course:	0-2 mm
Dry bulk density in hardened mortar:	1750 kg/m ³ ± 5% acc. PN-EN 998-1:2016
Mixing ratio:	5,5-5,6 l of water per 25 kg
Mixing time:	approx.2-3 minutes+5 minutes maturing time+ 1 minute
Application temperature range:	from +5°C up to +30°C
Working time:	up to 2 h
Compressive strength (category):	CS IV acc. PN-EN 998-1:2016
Adhesion to substrate and with fracture pattern:	≥ 0,5 MPa FP:B acc. EN 998-1:2016
Water absorption:	W _{c2} acc. PN-EN 998-1:2016
Water vapour permeability μ:	≤ 65 (saturated solution of KNO ₃) ≤ 80 (saturated solution of LiCl) acc. PN-EN 998-1:2016
Thermal conductivity λ _{10,dry} :	0,44 W/(m·K) acc. PN-EN 998-1:2016
Reaction to fire:	Class A1 acc. PN-EN 13501
Water penetration after 1h (tested on discs):	>5 mm acc. WTA 2-9-04/D
Water penetration after 24h (tested on discs):	>20 mm acc. WTA 2-9-04/D
Consumption:	approx. 5,0 kg/m ² net -shaped with a surface coverage of 50% of full area

- General purpose rendering / rendering mortar. Product complies with PN-EN 998-1:2016. Declaration of Product nr 01787 issued 29.11.2022
- Complies with the requirements of the WTA Code of Practice 2-9-04/D „Restoration render systems“ issued by the Wissenschaftlich-Technische Arbeitsgemeinschaft für Bauwerkserhaltung und Denkmalpflege, WTA certificate issued 02.05.2023.

	
16 Henkel Polska Operations Sp. z o.o. 02-672 Warszawa, ul. Domaniewska 41 Ceresit CR 60 01787 EN 998-1:2016 1487 General purpose rendering/rendering mortar	
Reaction to fire	A1 Class
Water absorption	W _{c2}
Water vapour permeability μ	μ (saturated solution of KNO ₃) ≤ 65 μ (saturated solution of LiCl) ≤ 80
Adhesion	≥ 0,5 MPa FP:B
Thermal conductivity λ _{10,dry} :	0,44 W/(m·K)

Documents available on the website; <https://www.henkel-dop.com>



Henkel CEE
Erdbergstrasse 29
1030 Vienna
www.ceresit.com

Quality for Professionals