



LOCTITE® 5964™

November 2004

PRODUCT DESCRIPTION

LOCTITE® 5964™ provides the following product characteristics:

Technology	Silicone
Chemical Type	Silicone
Appearance (uncured)	Brown paste ^{LMS}
Components	One component - requires no mixing
Cure	Heat cure
Secondary Cure	VFM (Variable Frequency Microwave)
Application	Gasketing
Specific Benefits	Nonslumping

LOCTITE® 5964™ is designed to be easily dispensed and cured directly onto manufactured components to form cured-in-place compression gaskets. It is resistant to automotive underhood oils, ethylene glycol/water mixtures, and other fluids. This material has been specifically developed to be cured using forced air, convection heat, or using VFM (Variable Frequency Microwave) technology. Typical applications include radiator end tanks, front covers, ABS modules, engine and air bag control modules, engine compartment/firewall components, and timing belt covers.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.4
Flash Point - See SDS	
Flow, ISO 7390, mm	≤5 ^{LMS}
Extrusion Rate, g/min:	
Pressure 0.62 MPa, time 15seconds, temperature 25 °C:	
Semco Cartridge	50 to 200 ^{LMS}

TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 1 hour @ 150 °C

Physical Properties:

Shore Hardness, ISO 868, Durometer A	23 to 33 ^{LMS}
Elongation, ISO 37, %	500 to 800 ^{LMS}
Tensile Strength, ISO 37	N/mm ² ≥3.4 ^{LMS} (psi) (≥493)
Tensile Modulus, ISO 37	N/mm ² 0.98 (psi) (142)
Compression Set, ASTM D 395, Method B, %:	
Aged @ 177 °C for 22 hours	≥55 ^{LMS}
Aged @ 150 °C for 168 hours	40
Aged @ 135 °C for 1,008 hours	60
Compression Set Relaxation, Sealing force retained, %:	
Aged @ 150 °C for 1,008 hours:	
ASTM service fluid 105 oil	9

TYPICAL PERFORMANCE OF CURED MATERIAL

Adhesive Properties

Cured for 1 hour @ 150 °C, tested @ 22 °C

Lap Shear Strength, ISO 4587:

Aluminum	N/mm ² ≥2.75 ^{LMS} (psi) (≥399)
----------	--

TYPICAL ENVIRONMENTAL RESISTANCE

Heat Aging

Aged at temperature indicated and tested @ 22 °C

Aged @ 200 °C for 168 hours:

Change in Durometer, Points (Initial =)	5
Change in Tensile Strength, %	-17.5
Change in Elongation, %	-35
Visual	No Cracks

Typical Fluid Immersion Properties

Aged @ 150 °C for 70 hours:

ASTM IRM 902 oil:

Change in Durometer, Points (Initial =)	-6
Change in Tensile Strength, %	-21
Change in Elongation, %	-13
Volume Swell, %	15
Compression Set, %	23

ASTM service fluid 105 oil:

Change in Durometer, Points (Initial =)	-13
Change in Tensile Strength, %	-51
Change in Elongation, %	-27
Volume Swell, %	46
Compression Set, %	0

Aged @ 110 °C for 70 hours:

Ethylene glycol/water, 50:50:

Change in Durometer, Points (Initial =)	1
Change in Tensile Strength, %	-4
Change in Elongation, %	-7
Volume Swell, %	-1
Compression Set, %	33

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for use:

1. Product should be brought to room temperature before use.
2. For best performance bond surfaces should be clean and free from grease.
3. Excess material can be easily wiped away with non-polar solvents.
4. It is recommended that this product be heat cured at @ 150 °C for 10 minutes, or 4 minutes using variable



frequency microwave.

5. Actual cure schedule depends on mass and geometry of parts.

Loctite Material Specification^{LMS}

LMS dated March 16, 2004. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 2 °C to 8 °C. Storage below 2 °C or greater than 8 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\mu\text{m} / 25.4 = \text{mil}$

$\text{N} \times 0.225 = \text{lb}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{N/mm}^2 \times 145 = \text{psi}$

$\text{MPa} \times 145 = \text{psi}$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 2