

Technical Data Sheet

LOCTITE[®] AA 3662™

Known as LOCTITE[®] 3662™ December 2014

PRODUCT DESCRIPTION

LOCTITE[®] AA 3662[™] provides the following product characteristics:

Technology	Acrylic
Chemical Type	Urethane methacrylate
Appearance (uncured)	Transparent, yellow to light amber liquid ^{LMS}
Components	One component -
	requires no mixing
Viscosity	Medium
Cure	Ultraviolet (UV) light
Secondary Cure	Activator
Application	Bonding, Coating or Sealing

LOCTITE[®] AA 3662^{TM} is a single component, medium viscosity, UV anaerobic structural adhesive suitable for bonding a wide range of materials. The product cures when exposed to suitable ultraviolet radiation and can also bond surfaces treated with a surface activator. When cured, it is highly resistant to vibration and impact forces. LOCTITE[®] AA 3662^{TM} is used to bond, seal or coat metal and glass components in industrial applications. Typical uses include hard disk drive applications.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.13
Flash Point - See SDS	
Viscosity, Brookfield - RVT, 25 °C, mPa·s (cP):	
Spindle 4, speed 10 rpm	6,000 to 12,000 ^{LMS}
Ionic Contaminants, ppm:	
Chloride	≤250 ^{LMS}
Sulfate	≤100 ^{LMS}
Ionic Contaminants, ppb:	
Tin	≤500 ^{LMS}
Infrared Spectroscopy	To match standard ^{LMS}

TYPICAL CURING PERFORMANCE

LOCTITE[®] AA 3662TM can be cured when exposed to UV radiation of 365 nm. To obtain a full cure on surfaces exposed to air, radiation at 250 nm is also required. The speed of cure will depend on the UV intensity as measured at the product surface. Typical cure condition is <15 seconds at 100mW/cm² using a medium pressure, quartz envelope, mercury vapour UV lamp.

Fixture Time

UV fixture time is defined as the light e	exposure	time
required to develop a shear strength of 0.1 N/m	nm ² .	
UV Fixture Time, Glass microscope slides, seconds	S:	
25 mW/cm ² , measured @ 365 nm		
TYPICAL PROPERTIES OF CURED MATERIA	L	
Physical Properties:		
Coefficient of Thermal Expansion,		
ISO 11359-2, K ⁻¹ :		
5 T		

Pre Tg	104×10⁻6
Post Tg	295×10 ⁻⁶
Glass Transition Temperature, ISO 11359-2, °C	58
Shore Hardness, ISO 868, Durometer D	70

Cured @ 150 mW/cm² , measured @ 365 nm, for 30 seconds, tested @ 85 $^\circ\text{C}$ for 2 hours.

Physical Properties

Outgassing, % Weight Loss

≤1^{LMS}

TYPICAL PERFORMANCE OF CURED MATERIAL Adhesive Properties

Cured for 24 hours @ 22 °C, Activator 7649™ on 2 sides Shear Strength Lap Shear Strength, ISO 4587: Steel (grit blasted) N/mm² ≥10.3^{Lh}

N/mm² ≥10.3^{LMS} (psi) (≥1,493)

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected with a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).



Directions for use:

- 1. This product is light sensitive; exposure to daylight, UV light and artificial lighting should be kept to a minimum during storage and handling.
- 2. The product should be dispensed from applicators with black feedlines.
- 3. For best performance bond surfaces should be clean and free from grease.
- 4. Cure rate is dependent on lamp intensity, distance from light source, depth of cure needed or bondline gap and light transmittance of the substrate through which the radiation must pass.
- 5. Recommended intensity for cure in bondline situation is 40 mW/cm² minimum (measured at the bondline) with an exposure time of 4-5 times the fixture time at the same intensity.
- For dry curing of exposed surfaces, higher intensity UV is required (100 mW/cm²).
- 7. Cooling should be provided for temperature sensitive substrates such as thermoplastics.
- 8. Plastic grades should be checked for risk of stress cracking when exposed to liquid adhesive.
- 9. Excess uncured adhesive can be wiped away with organic solvent (e.g. Acetone).
- 10. Bonds should be allowed to cool before subjecting to any service loads.

Loctite Material Specification^{LMS}

LMS dated March 15, 2001. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. **Storage below 8** °C or **greater than 28** °C **can adversely affect product properties**. Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

 $(^{\circ}C \times 1.8) + 32 = ^{\circ}F$ kV/mm x 25.4 = V/mil mm / 25.4 = inches μ m / 25.4 = mil N x 0.225 = lb N/mm x 5.71 = lb/in N/mm² x 145 = psi MPa x 145 = psi N·m x 8.851 = lb·in N·m x 0.738 = lb·ft N·mm x 0.142 = oz·in mPa·s = cP

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. [®] denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.2