

LOCTITE® ABLESTIK 546S04

November 2024

PRODUCT DESCRIPTION

LOCTITE® ABLESTIK 546S04 provides the following product characteristics:

Technology	Acrylate
Color	Off white liquid
Color (mixed)	Cream
Color (cured)	Light gray
Cure	Ultraviolet (UV) light followed by heat cure
Product benefits	<ul style="list-style-type: none"> Thixotropic
Application	Component assembly, NCA

LOCTITE® ABLESTIK 546S04 is ideal for general optics bonding, mounting of lenses and glob top applications. This adhesive exhibits bond strength retention after 85°C / 85% relative humidity exposure.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, CP52, mPa·s (cP):

Speed @ 10 rpm 11,400

Specific gravity, cured 1.7

Pot life, days 5

Flash point - see SDS

TYPICAL CURING PERFORMANCE

Recommended UV cure condition

Light source and condition:

Ultraviolet (UV) light

Exposure time, minutes 1.25

Light intensity, mW/cm 30

Secondary thermal cure condition

15 minutes @ 120°C

The above cure profile is a guideline recommendation. Actual cure time will vary depending on equipment used, focal distance and light intensity.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical properties

Hardness, Shore D 88

Coefficient of thermal expansion, ppm/°C

Below Tg, (-30 to 0°C) $2.30 \times 10^{+01}$

Above Tg, (100 to 150°C) $1.23 \times 10^{+02}$

Glass transition temperature, by DSC, ultimate, °C 48

TYPICAL PERFORMANCE OF CURED MATERIAL

Shear strength

Lap shear strength alum to alum, sample cured 15 minutes @ 120°C

N/mm ²	9.65
(psi)	(1,400)

GENERAL INFORMATION

Please consult the Safety Data Sheet (SDS) for safe handling information of this product.

Directions for use

- Carefully clean and dry all surfaces to be bonded.
- If packaged in BIPAX, remove clamp and thoroughly mix the LOCTITE® ABLESTIK 546S04 epoxy adhesive system components in the handy BIPAX mixing-dispenser package until color is uniform throughout.
- If pre-mixed and frozen, thaw adhesive to room temperature. A 25°C water bath is recommended.
- Apply this completely mixed adhesive to the prepared surfaces, and gently press these surfaces together. Contact pressure is adequate for strong, reliable bonds ;however, maintain contact until adhesive is completely cured.
- Cure at recommended cure schedules.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal storage: 27°C for BIPAX package, -40°C or colder for pre-mixed package

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

The expiration date for pre-mixed and frozen materials is based upon dry storage conditions at or below the temperature indicated on each package.

Contents may separate during storage. Resin or hardener in bulk containers (e.g., quarts, gallons) should be thoroughly mixed prior to combining them to obtain all the benefits of the properties designed into the formulation.

Some ingredients in this formulation provided in BIPAX,TRA-PAX and bulk packaging may crystallize when subjected to low temperature storage. Merely returning the product back to room temperature will not always redissolve the crystals and a gentle warming cycle of 50°C for 30 minutes prior to mixing the resin and hardener components may be necessary to return the product to its best condition. Crystallized epoxy components do not react as well as liquid components and should be redissolved prior to use for best result.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on the specifications of this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 2