

# LOCTITE ABLESTIK ABP 8064T

June 2020

## PRODUCT DESCRIPTION

LOCTITE ABLESTIK ABP 8064T provides the following product characteristics:

<b>Technology</b>	Hybrid chemistry
<b>Appearance</b>	Silver
<b>Product Benefits</b>	<ul style="list-style-type: none"> <li>• High thermal conductivity</li> <li>• High electrical conductivity</li> <li>• Medium modulus</li> <li>• Low outgassing</li> <li>• Stable at high temperatures</li> <li>• Good reliability performance</li> <li>• Soft solder replacement</li> <li>• Use for wide range of package sizes</li> </ul>
<b>Cure</b>	Heat cure
<b>Application</b>	Die attach
<b>Typical Package Application(s)</b>	QFP, High power devices

LOCTITE ABLESTIK ABP 8064T highly filled, conductive die attach adhesive is designed to provide high thermal and electrical conductivity in the attachment of integrated circuits and components onto metal leadframes.

LOCTITE ABLESTIK ABP 8064T passes NASA outgassing standards.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Filler Content %	85
Thixotropic Index (0.5/5 rpm)	5.8
Viscosity, Brookfield CP51, 25 °C, mPa·s (cP):	
Speed 5 rpm	12,000
Work Life @ 25°C, hours	24
Shelf Life @ -40°C (from date of manufacture), days	365

## TYPICAL CURING PERFORMANCE

### Recommended Cure Schedule

60 min ramp from 25°C to 180°C, hold 60 mins @ 180°C in N2 oven

### Alternative Cure Schedule

60 min ramp from 25°C to 140°C, hold 60 mins @ 140°C in N2 oven

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties

Coefficient of Thermal Expansion, TMA:	
Alpha 1, ppm/°C	47
Alpha 2, ppm/°C	136
Glass Transition Temperature (Tg) by TMA, °C	44.5
Tensile Modulus, DMTA :	
@ 25 °C	N/mm <sup>2</sup> 5,260 (psi) (762,900)
@ 250 °C	N/mm <sup>2</sup> 1,280 (psi) (185,505)
Extractable Ionic Content @ 100°C, :	
Chloride (Cl <sup>-</sup> )	<10
Sodium (Na <sup>+</sup> )	<10
Potassium (K <sup>+</sup> )	<10
Thermal Conductivity, W/m·°C	22

### Electrical Properties

Volume Resistivity, , ohm-cm	2.0×10 <sup>5</sup>
------------------------------	---------------------

## TYPICAL PERFORMANCE OF CURED MATERIAL

### Die Shear Strength:

3 X 3 mm (120 x 120 mil) Si die on PPF LF, Kg:	
@ 25°C	12.18
@ 260°C	5.6
5 X 5 mm (200 x 200 mil) Si die on PPF LF, Kg:	
@ 260°C	12.19
8 X 8 mm (300 x 300 mil) Si die on PPF LF, Kg:	
@ 260°C	18.54

## TYPICAL ENVIRONMENTAL RESISTANCE

### Outgassing Properties

Outgassing :	
TML, %	0.25
CVCM, %	0.05
WVR, %	0.02

## GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

### STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage : -40 °C**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

#### Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb/F}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{psi} \times 145 = \text{N/mm}^2$

$\text{MPa} = \text{N/mm}^2$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

more United States or foreign patents or patent applications.

#### Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.3

#### Disclaimer

##### Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

#### In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

#### In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

#### In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or

Americas  
+1.888.943.6535

Europe  
+32.1457.5611

Asia  
+86.21.2891.8000

**For the most direct access to local sales and technical support visit: [www.henkel.com/electronics](http://www.henkel.com/electronics)**