

LOCTITE® ABLESTIK NCA 2050

November 2021

PRODUCT DESCRIPTION

LOCTITE® ABLESTIK NCA 2050 provides the following product characteristics:

| | |
|-------------------------|--|
| Technology | Acrylate |
| Appearance | Pink liquid |
| Product Benefits | <ul style="list-style-type: none"> • One component • Good impact resistance • Good adhesion to various substrates |
| Cure | Ultraviolet (UV) light, Visible light |
| Application | Electronic Adhesives & Solder, Component assembly |

LOCTITE® ABLESTIK NCA 2050 one part, UV cure adhesive is specially formulated to provide excellent adhesion to a wide variety of substrates including glass, most metals and plastics.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield CP51, 25 °C, mPa·s (cP):
 Speed 5.0 rpm 6,400
 Thixotropic Index (0.5/5.0 rpm) 5.3

TYPICAL CURING PERFORMANCE**Recommended Cure Condition****UV Light**

UV Wavelength, nm 285 to 405
 Light Intensity, mW/cm² 1,000
 Exposure Time, seconds >10

Cure rate and depth of cure depends both on external factors including the type of light source, light intensity and exposure time, and on internal factors including composition of the adhesive.

The above cure profile is a guideline recommendation. Cure rate and ultimate depth of cure depend on light intensity, spectral distribution of light source, exposure time and the light transmittance of the substrate.

TYPICAL PROPERTIES OF CURED MATERIAL**Physical Properties**

Sample cured UV 365 nm, UV intensity 10,000 mJ/cm².

Hardness, Shore D 36
 Glass Transition Temperature, (Tg) by TMA, °C 43
 Coefficient of Thermal Expansion :
 Below Tg, ppm 130
 Above Tg, ppm 257
 Elongation @ break, % 230
 Storage Modulus @ 25°C, DMA, N/mm² 484
 Moisture Absorption, % 4.8
 Volume Shrinkage, % 6.6

Adhesion Properties

Sample cured UV 365 nm, UV intensity 10,000 mJ/cm².
 Adhesion Strength, Fr5 substrate, kg-f 12.2

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

THAWING: (if applicable)

1. Safe yellow light is recommended for visible light initiated grades during handling prior to curing. Dimmed light may be used if adhesive is only being handled for short periods of time.
2. Allow container to reach room temperature before use.
3. After removing from the freezer, set the syringes to stand vertically while thawing.
4. DO NOT open the container before contents reach 25 °C temperature. Any moisture that collects on the warmed up container should be removed prior to opening the container.
5. DO NOT re-freeze. Once thawed, the adhesive should not be re-frozen.

Directions for Use

1. Thawed material should immediately be placed on dispense equipment for use.
2. If the adhesive is transferred to a final dispensing reservoir, care must be exercised to avoid entrapment of contaminants and/or air into the adhesive..
3. Adhesive must be completely used within the product's recommended work life.
4. This product is light sensitive; exposure to daylight, UV light or artificial lighting should be kept to a minimum during storage and handling.



STORAGE

Store in original, tightly covered containers in clean, dry areas. Storage information may be indicated on the product container labeling.

Optimal Storage: 2 to 8°C. Storage below 2°C or above 8°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local Henkel representative for assistance and recommendations on the specifications of this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb/F}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1