

# LOCTITE ABLESTIK NCA 2200

September 2022

## PRODUCT DESCRIPTION

LOCTITE ABLESTIK NCA 2200 provides the following product characteristics:

<b>Technology</b>	Acrylated Epoxy
<b>Appearance</b>	Light yellow liquid
<b>Product Benefits</b>	<ul style="list-style-type: none"> <li>• One component</li> <li>• Dual cure system</li> <li>• Low viscosity</li> <li>• Fast cure at low temperature</li> <li>• Non-conductive</li> <li>• Good adhesion to a variety of substrates</li> </ul>
<b>Cure</b>	Ultraviolet (UV) light followed by heat cure
<b>Application</b>	Assembly
<b>Key Substrates</b>	Ceramics, LCP and Stainless steel
<b>Typical Assembly Applications</b>	Image sensor module assemblies

LOCTITE ABLESTIK NCA 2200 dual cure adhesive is designed for use in the assembly of temperature sensitive electronic components

This product is formulated to temporarily cure when exposed to UV light, followed with a secondary thermal cure at low temperature. Temporarily curing the material allows for any necessary adjustments to the final device configuration.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Rheometer, Cone and Plate @ 25°C, mPa·s (cP):	
Cone 20 mm, Angle 2° @ Shear rate 20 s <sup>-1</sup>	22,000
Thixotropic Index (2/20 s <sup>-1</sup> )	2
Specific Gravity, g/cm <sup>3</sup>	1.3
Pot Life @ 25°C, days	3
Shelf Life @ -20°C (from date of manufacture), days	365
Flash Point - See SDS	

## TYPICAL CURING PERFORMANCE

### Recommended UV Cure

Light Source and Condition	
High pressure mercury lamp:	
UV Wavelength, nm	220 to 380
Light Intensity, mW/cm <sup>2</sup>	100
Exposure Time	2

### Recommended Heat Cure Schedule

30 minutes @ 80°C

## Depth of Cure

Sample tested using High pressure mercury lamp with light intensity of 100 mW/cm<sup>2</sup>

Exposure Time, mm:	
@ 2 seconds	0.7
@ 10 seconds	1.5
@ 20 seconds	1.6
@ 30 seconds	1.6

With all curing systems, the time required for cure depends on the rate of heating. Cure rate depends on the mass of material to be heated and intimate contact with the heat source. Use suggested cure conditions as general guidelines. Other cure conditions may yield satisfactory results.

The above cure profile is a guideline recommendation. Cure rate and ultimate depth of cure depend on light intensity, spectral distribution of light source, exposure time and the light transmittance of the substrate.

## TYPICAL PROPERTIES OF CURED MATERIAL

Sample cured at the recommended cure conditions.

### Physical Properties

Hardness, Shore D	90
Coefficient of Thermal Expansion, ppm/°C:	
Below Tg	43
Above Tg	150
Glass Transition Temperature (Tg) by TMA, °C	97
Modulus @ 25°C	GPa 5
	(N/mm <sup>2</sup> ) (0,005)
	(psi) (0,725)

## TYPICAL PERFORMANCE OF CURED MATERIAL

### Shear Strength

Die Shear Strength:	
LCP, SiN Chip	N/mm <sup>2</sup> 20
	(psi) (2,900)
SUS304, SiN Chip	N/mm <sup>2</sup> 50
	(psi) (7,251)

## GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

## STORAGE

Store in original, tightly covered containers in clean, dry areas. Storage information may be indicated on the product container labeling.

Optimal Storage : -20 °C



Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

#### Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb/F}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{N/mm}^2 \times 145 = \text{psi}$

$\text{N/mm}^2 = \text{MPa}$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

#### Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.1

#### Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

#### **In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

#### **In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

#### **In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.