

LOCTITE D 125 F 5

June 2020

PRODUCT DESCRIPTION

LOCTITE D 125 F 5 provides the following product characteristics:

Technology	Epoxy
Appearance	Yellow
Components	One part - requires no mixing
Product Benefits	• Low exotherm • Low water absorption • High hot strength • High green strength • No sag during cure • No moisture absorption when uncured • No corrosion after cure • Low temperature cure
Cure	Heat cure
Application	Electronic Material, Component assembly
Operating Temperature	120 °C
Typical Assembly Applications	SOICs and PLCCs

LOCTITE D 125 F 5 surface mount adhesive is designed for use in high-speed pneumatic and positive displacement dispensers.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Calculated Yield (Bingham), N/m ²	700
Density, g/cm ³	1.4
Fineness, µm	<50
Storage Life (from date of manufacture):	
@ 0 to 8°C, days	180
@ 18 to 25°C, days	60
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE**IR or Convection Conveyor Oven**

20 minutes @ 100°C or
7 minutes @ 110°C or
2.5 minutes @ 120°C

Convection Box Oven

30 minutes @ 100°C or
20 minutes @ 110°C or
10 minutes @ 120°C

LOCTITE D 125 F 5 can be cured using infrared systems or convection oven.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL**Physical Properties**

Coefficient of Thermal Expansion, 10 ⁻⁶ K ⁻¹	58
Glass Transition Temperature, °C	73
Degree of Conversion @ 125°C, %	>90
Linear Shrinkage on Cure, %	0.5
Hardness, Shore D	>80
Thermal Conductivity, W/(m-K)	0.3

Electrical Properties

Volume Resistivity, ohm-cm	>1×10 ¹⁴
Dielectric Constant	3.5

TYPICAL PERFORMANCE OF CURED MATERIAL

Tensile Lap Shear Strength	N/mm ² >6 (psi) (>870)
----------------------------	--------------------------------------

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

DIRECTIONS FOR USE

1. Store in a cool, clean and dry area.
2. Usable shelf life may vary depending on method of application and storage conditions.
3. LOCTITE D 125 F 5 stored at low temperatures must be allowed to return to room temperature before use. This normally takes 8 to 12 hours.
4. For board and equipment cleaning we advise the use of LOCTITE STYCAST CLEANER 50306.
5. Use of alcohol for cleaning is not recommended.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 0 to 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb/F}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1