

LOCTITE ECCOBOND D 125 F DR

December 2018

PRODUCT DESCRIPTION

LOCTITE ECCOBOND D 125 F DR provides the following product characteristics:

Technology	Epoxy
Appearance	Dark red
Components	One-component
Product Benefits	<ul style="list-style-type: none"> • Low exotherm • Low water absorption • High hot strength • No foaming • No corrosion • High speed dispensing without stringing • No loss of components during wave soldering • High yield • No sag during cure
Cure	Heat Cure
Application	Component assembly, NCA
Operating Temperature	120 °C
Typical Assembly Applications	Chip capacitors, Chip resistors, SOTs, SOICs and PLCCs

LOCTITE ECCOBOND D 125 F DR surface mount adhesive is designed for use in high-speed pneumatic and positive displacement dispensers. This one component adhesive is formulated to prevent component movement during board handling and cure. LOCTITE ECCOBOND D 125 F DR is the red colored version of LOCTITE ECCOBOND D125F.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Plastic Viscosity (Bingham), mPa·s (cP)	37,000
Calculated Yield (Bingham), N/m ²	350
Density ASTM D792, g/cm ³	1.275
Fineness, µm	<50
Shelf Life, days:	
@ 0 to 8°C	183
@ 18 to 25°C	60
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE

IR or Convection Conveyor Oven

20 minutes @ 100°C or
7 minutes @ 110°C or
2.5 minutes @ 120°C

Convection Box Oven

30 minutes @ 100°C or
20 minutes @ 110°C or
10 minutes @ 120°C

Note: A ramp up temperature of not more than 1°C per second should be used.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Hardness, Shore D	>80
Glass Transition Temperature, °C	85
Coefficient of Thermal Expansion, 10 ⁻⁶ K ⁻¹	55 to 60
Degree of Conversion after 3 minutes @ 125°C, %	>90
Linear Shrinkage on Cure, %	0.5
Thermal Conductivity, W/(m·K)	0.3

Electrical Properties

Dielectric Constant	3.5
Volume Resistivity, ohm-cm	>1×10 ¹⁴
Electromigration (Bellcore)	Pass

TYPICAL PERFORMANCE OF CURED MATERIAL

Tensile Lap Shear Strength	N/mm ²	>7
	(psi)	(>1,020)

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

1. LOCTITE ECCOBOND D 125 F DR is best suited for dispensing, pin transfer or stencil printing application method.
2. Equipment set-up and related product information is available from your Henkel Corporation support group.
3. NOTE: Heat up to 40°C to decrystallise product (maximum 3 hours, depending on packaging).

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 0 to 8 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 1