

# LOCTITE ECCOBOND DAM 7010C

April 2020

## PRODUCT DESCRIPTION

LOCTITE ECCOBOND DAM 7010C provides the following product characteristics:

<b>Technology</b>	Epoxy
<b>Appearance</b>	Black
<b>Components</b>	One-component
<b>Cure</b>	Heat cure
<b>Product Benefits</b>	<ul style="list-style-type: none"> <li>• Crack and thermal resistant</li> <li>• Good chemical resistance</li> <li>• Low thermal expansion</li> <li>• High purity</li> <li>• Non-sag</li> </ul>
<b>Operating Temperature</b>	-40 to 150°C
<b>Application</b>	Encapsulants, Semiconductor Encapsulant (SCE)
<b>Typical Applications</b>	Glob top applications, Wire bonded bare IC protection

LOCTITE ECCOBOND DAM 7010C is formulated to be used in combination with a "fill" encapsulant LOCTITE ECCOBOND FIL 7010C as a dam encapsulant. It is specially designed for glob top applications where protection of wire bonded bare IC is required.

This two material combination is also suited for the protection of multiple chips and for encapsulating components where a well-defined glob height and flat surface are required.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity @ 25 °C, mPa·s (cP):	
@ 15 s <sup>-1</sup>	80,000 to 105,000
Thixotropic Index	≥3
Density, gm/cc	1.9
Shelf Life:	
@ -40 °C, days	180
@ 25°C, day	1
Flash Point - See SDS	

## TYPICAL CURING PERFORMANCE

### Recommended Cure Schedule

2 hours @ 140°C

### Low Stress Cure Schedule

1 hour @ 100°C plus 1 hour @ 150°C

The above cure profile is a guideline recommendation. These cure conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties

Hardness, Shore D	≥90
Glass Transition Temperature(Tg), °C:	
(Tg) by DMA	130 to 140
(Tg) by TMA	135 to 145
Coefficient of Thermal Expansion, 10 <sup>-6</sup> /°C:	
Below Tg	14 to 18
Above Tg	60 to 65
Young's modulus (E) @ 25°C, GPa	11
Thermal Conductivity, W/(m-K)	0.78
Extractable Ionic Content @ °C, , ppm:	
Chloride (Cl-)	≤10
Potassium (K+)	≤10
Sodium (Na+)	≤10
Ammonia (NH <sub>3</sub> +) )	≤10
Water Absorption , %:	
24-hour boil test by weight	0.45

### Electrical Properties

Volume Resistivity , ohms-cm	8.96×10 <sup>+15</sup>
Surface Resistivity, ohms	5.9×10 <sup>+15</sup>
Dielectric Strength, kV/mm	>20
Dielectric Constant/Dissipation Factor @ 1 MHz	3.6/0.015

## GENERAL INFORMATION

**For safe handling information on this product, consult the Safety Data Sheet, (SDS).**

### Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

### THAWING:

1. Allow container to reach room temperature before use.
2. DO NOT open the container before contents reach 25°C temperature. Any moisture that collects on the thawed container should be removed prior to opening the container.
3. DO NOT re-freeze. Once thawed, the adhesive should not be re-frozen.

**Directions for use**

1. Cure the product per the cure schedule mentioned in the Typical Cure Schedule section of the document.
2. The surfaces on which the adhesive has to be applied should be clean, dry and free from all dust.
3. Initially dispense LOCTITE ECCOBOND DAM 7010C on the outline of the glob referred to as the "dam".
4. The dam is then filled in with LOCTITE ECCOBOND FIL 7010C material.
5. Both materials can be co-cured after dispense.

**Storage**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage : -40 °C**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\text{N} \times 0.225 = \text{lb/F}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{psi} \times 145 = \text{N/mm}^2$   
 $\text{MPa} = \text{N/mm}^2$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana,**

**S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1