

# LOCTITE ECCOBOND LUX 4047

December 2014

## PRODUCT DESCRIPTION

LOCTITE ECCOBOND LUX 4047 provides the following product characteristics:

<b>Technology</b>	Acrylate
<b>Color</b>	Opaque White
<b>Cure</b>	Ultraviolet (UV) light
<b>Product Benefits</b>	<ul style="list-style-type: none"> <li>• Single component</li> <li>• Photocurable</li> <li>• High viscosity</li> <li>• Low shrinkage</li> <li>• Good mechanical stability</li> </ul>
<b>Application</b>	Assembly
<b>Typical Optic Application</b>	Fiber optic assembly and Optoelectronic device assembly
<b>Other Application Areas</b>	LED mounting, Laser diode packaging, Fiber pigtail and Transceiver potting

LOCTITE ECCOBOND LUX 4047 photocurable adhesive is designed for high throughput optoelectronic assembly operations. This adhesive cures in seconds when exposed to the appropriate intensity of visible (blue) or UV light.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity @ 25 °C, mPa·s (cP):	
Small sample adapter	120,000
Shelf Life:	
@ 5°C, months	6
@ 25°C, months	3
Flash Point - See SDS	

## TYPICAL CURING PERFORMANCE

### Recommended Cure

UV or visible light

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties

Hardness, Shore D	80
Coefficient of Linear Expansion:	
Below Tg, in/in/°C	20×10 <sup>-6</sup>
Above Tg, in/in/°C	75×10 <sup>-6</sup>
Glass Transition Temperature (Tg), °C:	
DMTA Loss of Modulus	52
DMTA Tan Δ Max	148
Flexural Modulus	N/mm <sup>2</sup> 7,901 (psi) (1,146,000)
Linear Shrinkage on Cure, %	1.1
Water Absorption, 24-hr immersion, %	0.07

## TYPICAL PERFORMANCE OF CURED MATERIAL

Lap Shear Strength @ 25°C, psi:

Glass to Glass 1,200

## GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

### THAWING:

1. DO NOT open the package before contents reach ambient temperature.
2. Safe yellow light is recommended for visible light initiated grades during handling prior to curing. Dimmed light may be used if adhesive is only being handled for short periods of time.

## DIRECTIONS FOR USE

1. This adhesive is formulated to cure upon exposure to visible (blue) or UV light. Curing with visible light allows curing of highly filled (up to 80% by weight) grades and curing through UV opaque substrates (such as Polycarbonate or Alumina). Use of visible light provides increased operator safety by eliminating exposure to potentially harmful UV radiation. UV curing is particularly advantageous where a very rapid cure of a section is required.
2. For visible light curing, a light source with a peak output at 470 nm is most efficient. For example, a Luxor 2 or 3 curing lamp delivers an output in excess of 150 mW/cm<sup>2</sup> at this wavelength, curing in <1 minute to a depth of 12 mm unfilled and 5 mm in filled grades.
3. For UV cure, a wide range of commercially available lamp systems are available, permitting curing of bond profiles in seconds coupled with a tack-free surface.

## AVAILABILITY

1. This adhesive is available in a variety of syringes, ranging from 2.5ml to 10ml.

### Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

### STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 25°C. Storage below 5°C or greater than 25°C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions** $(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$  $\text{kV/mm} \times 25.4 = \text{V/mil}$  $\text{mm} / 25.4 = \text{inches}$  $\text{N} \times 0.225 = \text{lb}$  $\text{N/mm} \times 5.71 = \text{lb/in}$  $\text{psi} \times 145 = \text{N/mm}^2$  $\text{MPa} = \text{N/mm}^2$  $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$  $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$  $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$  $\text{mPa}\cdot\text{s} = \text{cP}$ **Disclaimer****Note**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel, is therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation

that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1