

LOCTITE ECCOBOND UF 4550HTC

August 2021

PRODUCT DESCRIPTION

LOCTITE ECCOBOND UF 4550HTC provides the following product characteristics:

Technology	Epoxy
Color	Off white liquid
Filler Type	Alumina
Filler Weight, %	75
Product Benefits	- Thermally conductive - High TG, low CTE - Low ionics - Fast flow - Fast cure @ 160°C - Jet dispensable
Cure	Heat cure
Application	Underfill
Typical Package Application(s)	- High thermal applications - Flip chip devices - Flexible circuits

LOCTITE ECCOBOND UF 4550HTC is a board level capillary underfill designed to provide enhanced thermal properties and adhesion to integrated circuit passivation material and flex circuits. LOCTITE ECCOBOND UF 4550HTC is designed to quickly underfill at elevated substrate temperature of 90 to 110°C. LOCTITE ECCOBOND UF 4550HTC provides thermal conductivity for applications where thermal management is required. This material is also engineered to provide good thermal cycle reliability for PCBAs.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield - Cone & Plate CP51, 25 °C, mPa·s (cP):

@ Speed 0.5 rpm	12,000
@ Speed 5.0 rpm	13,800

Thixotropic Index (0.5/5.0 rpm) 0.9

Specific Gravity, Pycnometer 2.47

Flow Rate @ 100°C, mm:

@ 2 mil gap, 12 mm wide, 15 seconds 6

Shelf Life @ -40°C (from date of manufacture), days 271

Work Life @ 25°C, hours 12

Flash Point - See SDS

TYPICAL CURING PERFORMANCE

Cure Schedule

15 minutes @ 160°C

The above cure profile is a guideline recommendation. These cure conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Coefficient of Thermal Expansion, TMA:

Below Tg, ppm/°C	23
Above Tg, ppm/°C	102

Glass Transition Temperature (Tg) by TMA, °C 143

Flexural Modulus, DMA, single cantilever:

@ 25°C	N/mm ²	10,100
	(psi)	(1.46×10 ⁶)
@ 250°C	N/mm ²	178
	(psi)	(25,800)

Moisture Absorption, 85°C/85% RH, % 0.5

Extractable Ionic Content, 24 hours @ 100°C, ppm:

Sodium (Na+)	1
Potassium (K+)	<0.5
Chloride (Cl-)	8

Thermal Conductivity, Laser Flash, W/(m·K) 1.2

Adhesive Properties

Die Shear Strength, Dage Tester, kg-f:

120 x 120 mil die on Si/BT:	
@ 25 °C	43
@ 260 °C	2.8

GENERAL INFORMATION

Please consult the Safety Data Sheet (SDS) for safe handling information of this product.

DIRECTIONS FOR USE

1. Allow material to thaw @ 25°C for at least 45 minutes
2. For best flow rates, a preheat temperature of 90 to 110 °C is recommended.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: -40 °C. Storage below minus (-)40 °C or greater than minus (-)40 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb/F}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local Henkel representative for assistance and recommendations on the specifications of this product.

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Reference 2