

LOCTITE EDAG 109 E&C

April 2023

PRODUCT DESCRIPTION

LOCTITE EDAG 109 E&C provides the following product characteristics:

Technology	Thermoplastic
Appearance	Black liquid
Filler Type	Carbon
Product Benefits	<ul style="list-style-type: none"> Fast drying Extremely flexible Conductive
Cure	Heat drying
Application	Conductive Ink
Operating Temperature-Maximum	105°C
Typical Assembly Applications	Electronic circuitry, RFID antenna, Hearing elements and Bio and medical sensors
Key Substrates	Plastics and Paper substrates

LOCTITE EDAG 109 E&C is designed for applications using flexographic or rotogravure techniques. This product is fully miscible with LOCTITE EDAG SP 413 E&C silver ink to produce a wide range of resistances.

TYPICAL PROPERTIES OF UNDRIED MATERIAL

Solids Content, %	40
Viscosity, Brookfield, mPa·s (cP):	
Speed 20 rpm, @ 25°C	2,200
Density, kg/cm ³	1,030
Theoretical coverage, m ² /kg:	
@ 10µm dry coating thickness	22
Shelf Life, from date of qualification in original seal, days	365
Flash Point, °C	14

TYPICAL DRYING CYCLE

Recommended Drying Cycle

15 to 30 minutes @ 70 to 80°C

LOCTITE EDAG 109 E&C can be dried with forced air or infrared systems. Higher temperatures for longer time will improve the performance. However, care should be taken with infrared. Too much energy can destroy the coating. Design drying rates for the maximum the substrate and production speeds can tolerate.

The above cure profile is a guideline recommendation. These cure conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF DRIED MATERIAL

Physical Properties

Pencil hardness	HB
-----------------	----

Electrical Properties

Sheet Resistance Ohm/sq/25µm	≤15
------------------------------	-----

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

Surface Preparation

- Surfaces to be coated must be clean, dry and free of dust.

Mixing/Dilution

- Before use, the material should be mixed thoroughly using a mechanical stirrer or paint shaker until it is of uniform consistency. Check to see that no sediment remains in the bottom of the container.
- Pour in a suitable container in case dilution is required.

Application

LOCTITE EDAG 109 E&C may be applied by spray, brush or print method.

• SPRAY APPLICATION

- If dilution is necessary, use MEK or MIBK.
- Use a ratio of 1:1 product to diluent by weight for dilution.
- To dilute, add solvent to LOCTITE EDAG 109 E&C and continue stirring until mixture is of uniform colour.
- LOCTITE EDAG 109 E&C is applied using conventional padde agitated pressure tank spray systems. Recommended spray pressure is 2 to 2.5 bar with a spray gun nozzle diameter of 1 to 2 mm.
- Small prototype runs may be sprayed with suction sup spray equipment.

• BRUSH APPLICATION

- LOCTITE EDAG 109 E&C can be applied by brush as supplied.

• PRINT APPLICATION

- LOCTITE EDAG 109 E&C is supplied ready for use. Should thinning become necessary, use MEK or MIBK.

Drying

- This product air dries to touch in about 10 minutes and to handle in approximately 30 minutes, depending on ambient temperatures.
- For production runs, conventional forced drying methods may be used for faster processing.

CLEAN-UP

The screen and equipment can be cleaned with dilution solvent, or esters (butylacetate, propylacetate, or ethylacetate), or ketones (MEK, Acetone), or similar solvents.

STORAGE

Store product in the unopened container in a cool dry well ventilated area. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 to 28°C. Storage below 8°C or greater than 28°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local Henkel representative for assistance and recommendations on the specifications of this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb/F}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{N/mm}^2 \times 145 = \text{psi}$

$\text{N/mm}^2 = \text{MPa}$

$\text{N} \cdot \text{m} \times 8.851 = \text{lb} \cdot \text{in}$

$\text{N} \cdot \text{m} \times 0.738 = \text{lb} \cdot \text{ft}$

$\text{N} \cdot \text{mm} \times 0.142 = \text{oz} \cdot \text{in}$

$\text{mPa} \cdot \text{s} = \text{cP}$

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.3