

LOCTITE EDAG PD 054 E&C

October 2012

PRODUCT DESCRIPTION

LOCTITE EDAG PD 054 E&C provides the following product characteristics:

Technology	Acrylate
Appearance	Silver
Product Benefits	<ul style="list-style-type: none"> Electrically conductive UV curable Fast UV cure
Cure	Ultraviolet (UV) light followed by heat cure
Application	Conductive Ink
Typical Applications	Conductive label applications

LOCTITE EDAG PD 054 E&C electrically conductive silver ink is ideal for applications using solvent or heat sensitive substrates. It is suitable for applications using flexographic or rotogravure printing techniques.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Solids Content, %	100
Viscosity, Brookfield CP42, 25 °C, mPa·s (cP):	
Speed 50 rpm	800
Density, kg/l	2.68
Shelf Life @ 15°C (from date of qualification in original seal), months	6

TYPICAL SCREEN PRINTING PROCESS

Recommended Film Thickness	
Thickness, µm	8 to 13
Emulsion Thickness	
Solvent resistant emulsion, µm	20
Recommended Squeegee	
Polyurethane or other solvent resistant material :	
When used on Polyester Mesh, durometer	60
When used on Stainless Steel Mesh, durometer	70
Recommended Screen Type	
Polyester screen, mesh	330
Stainless steel screen, mesh	400

TYPICAL CURING PERFORMANCE

Recommended UV Cure	
Light Source:	
Fusion "D"	
IR shifted mercury bulb	
Light Intensity, J/cm ²	1.4
Recommended Heat Cure	
60 seconds @ 100°C	

For optimum performance, follow the initial UV cure with the recommended heat cure.

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Theoretical Coverage, m ² / l	39.3
--	------

Electrical Properties

Sheet Resistivity, ohms/sq/mil	<0.075
--------------------------------	--------

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

Mixing/Dilution

- Gently stir prior to each use, mixing well from the bottom of the container, avoiding excessive heat or air entrapment.
- LOCTITE EDAG PD 054 E&C is supplied ready for use.
- Should thinning become necessary, dilute 2% by weight with .
- Many factors influence the cured film thickness. These include snap-off distance, screen mesh size, squeegee material, screen material and emulsion thickness.

Application Details

- LOCTITE EDAG PD 054 E&C may be applied by rotogravure, flexographic or flatbed screen printing process method.
- A dry coating thickness up to 8 to 13 µm can be applied by selecting the proper anilox or gravures
- Typical anilox rolls are 120 line, 14 bcm, quad ruled or 140 line, 12 bcm trihelic rolls. Praxair ART 15BCM 200 line anilox rolls are best for this product
- 1 to 2 passes are required to build a film thickness of 13 µm
- Flexographic transfer plates can be half-toned or textured to enhance thicker film builds

CLEAN-UP

- To clean screen and equipment, use Methyl ethyl ketone (MEK) or similar solvents.
- Clean the mesh of the screen until free of all visible particles in the screen.
- Allow screen to completely dry before using again.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 15 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{psi} \times 145 = \text{N/mm}^2$

$\text{MPa} = \text{N/mm}^2$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others

over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1