

LOCTITE EDAG PF 006 E&C

August 2016

PRODUCT DESCRIPTION

LOCTITE EDAG PF 006 E&C provides the following product characteristics:

Technology	Thermoplastic
Appearance	Silver liquid
Cure	Heat cure
Product Benefits	<ul style="list-style-type: none"> Screen printable
Application	Conductive Ink

LOCTITE EDAG PF 006 E&C is a blend of silver and carbon in a thermoplastic resin system.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Solids Content by Weight, %	57
Viscosity @ 30 °C, mPa·s (cP):	
Spindle 6, speed 20 rpm	16,000
Density, kg/l	1.73
Shelf Life (from date of qualification in original seal), days	365
VOC, g/l	742
Flash Point, °C	107

TYPICAL CURING PERFORMANCE

Recommended Cure Schedule

5 minutes @ 120°C

This product can also be cured using infrared.

Low conductivity and poor adhesion can result from undercuring.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Theoretical coverage, m ² /kg	5.96
--	------

Electrical Properties

Resistivity, ohms/sq/mil	<0.02
--------------------------	-------

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

1. Mixing/Dilution

- LOCTITE EDAG PF 006 E&C is ready to use but should be mixed thoroughly using a plastic spatula.
- Mix smoothly from bottom of container, careful not to whip air in to the product. Using a plastic spatula will decrease the possibility of introducing plastic grindings from the container

sidewalls into the product, possibly clogging the screens

- LOCTITE EDAG PF 006 E&C should be at room temperature prior to use.

2. Screen Type

- Optimal performance of this product is achieved when printed at a cured thickness of 0.25-0.4 mils.
- Using a polyester screen with 160 to 200 mesh opening or a stainless steel with 170 to 325 mesh opening will achieve best results.
- A solvent-resistant emulsion of 0.5 to 1.5 mils is recommended.

Clean-up

To clean screen and equipment, use MEK or similar solvents. Clean the mesh of the screen until free of all visible particles in the screen. Allow screen to completely dry before using again.

Storage

Store product in the unopened container in a cool dry well ventilated area. Storage information may be indicated on the product container labeling.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

(°C x 1.8) + 32 = °F
 kV/mm x 25.4 = V/mil
 mm / 25.4 = inches
 N x 0.225 = lb
 N/mm x 5.71 = lb/in
 psi x 145 = N/mm²
 MPa = N/mm²
 N·m x 8.851 = lb·in
 N·m x 0.738 = lb·ft
 N·mm x 0.142 = oz·in
 mPa·s = cP

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1