

Description

Loctite® Frekote® 815-NC has been designed to form a semi-permanent release interface on mold surfaces with application temperatures from room temperature to 135°C (275°F). The non-migratory multiple release system chemically bonds to the mold surface to form a micro thin chemically resistant coating. Loctite® Frekote® 815-NC will release all natural and synthetic organic rubber compounds. It has minimal build-up on the mold surface and exhibits high thermal stability for all molding processes. During touch-up cycles where application temperatures are above 135°C (275°F) we recommend Loctite® Frekote® 800-NC.

Features

Room temperature application
No mold build-up
High thermal stability
Reduced reject rates
Releases most rubber compounds
Maximum mold utilization
Provides instant on line capability

Properties

Color	Clear liquid
Odor	Hydrocarbon
Solvents	Aliphatic Naphtha
Specific Gravity	0.750 +/- 0.020
Shelf Life	18 months from date of manufacture
Cured thermal stability	400°C (750°F)
Special Cautions	Moisture sensitive, keep container tightly closed when not in use.

Mold Preparation

The mold surface must be clean and free of any release agent or other contaminants for Loctite® Frekote® 815-NC to be completely effective. Remove any contaminants with Loctite Frekote PMC or other suitable cleaning solvents. Light industrial abrasives can be used to remove heavy resin build up.

New Molds Full curing of new molds is advisable to ensure the best bonding of Loctite® Frekote® 815-NC to the mold surface. New fiberglass and epoxy molds should be cured per manufacturer's instructions before starting full scale production.

Note For porous, green or repaired molds, a Loctite Frekote Sealer should be used - technical data is available. Consult with your Henkel Representative for assistance.

Application *Consult MSDS prior to use*

Loctite® Frekote® 815-NC may be applied by spraying (ensuring a dry air source), airless spray, brushing, dipping or wiping. When wiping, 100% cotton cloths should be used. Care should be taken to avoid contact with hands and eyes. Always use in a well, ventilated area.

1. Apply a light uniform coat of Loctite® Frekote® 815-NC. Always apply in a well, ventilated area and allow complete solvent evaporation. Wipe or spray on a smooth, thin, continuous wet film. Avoid wiping or spraying over the same area that was just coated until the solvents have evaporated.
2. Apply a second coat perpendicular to the first, again avoiding pool or run marks due to over application. Allow to fully dry for 10-15 minutes between coats at room temperature.
3. A total of three light coats should be applied. The final coating will cure within one hour at room temperature or the cure process may be accelerated by baking the dried coating at 60°C (140°F) or above for fifteen minutes, i.e. by bringing mold to processing temperature for high temperature processes.
4. Maximum releases will be obtained as the mold becomes conditioned to Loctite® Frekote® 815-NC. Performance will be improved by applying a touch-up coat of product after the first few multiple releases. Loctite® Frekote® 815-NC efficiency may be less in the process involving heavy filled polymers and additional touch-ups may be necessary in such areas.

Touch Up

Touch up coats should be applied at regular intervals determined by the operator. This will depend on the polymer type, mold configuration and abrasion parameters. Touch up coats will maintain the base coats, hence reduce the chance for compound or polymer build-up. In situations where application temperatures fall below 135°C (275°F), Loctite® Frekote® 815-NC is recommended. For application temperatures above 135°C (275°F), Loctite Frekote 800-NC is recommended.

Flammability/ Storage

Loctite® Frekote® 815-NC contains flammable solvents. The product should always be used in well ventilated areas. Store in a cool, dry place. Keep container tightly closed when not in use.

Note

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.