

LOCTITE M 3000-1RS E&C

March 2016

PRODUCT DESCRIPTION

LOCTITE M 3000-1RS E&C provides the following product characteristics:

Technology	Vinyl
Appearance	Black
Product Benefits	<ul style="list-style-type: none"> • One component • Processing Ease • Screen printable for reduction in circuit profile and production
Cure	Heat cure, Hot air drying or Infrared
Application	Conductive Ink
Diluent	Carbitol acetate

LOCTITE M 3000-1RS E&C is a series of graphite based, screen printable inks that can be blended together for a custom fixed resistor on flexible substrates such as polyester and polyimide. These inks are specifically designed for the application of resistive trace and fixed resistors on polyester and other flexible membrane materials.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield - HBT, 25 °C, mPa·s (cP):	
Spindle 14	35,000
Solids Content by Weight, %	45
Density, g/cm ³	1.3
Shelf Life @ 25 °C (from date of qualification in original seal), days	365
Flash Point, °C	70

TYPICAL SCREEN PRINTING PROCESS

Screen mesh:	
Stainless steel	200
Polyester screen	196
Minimum mesh opening, %	33
Squeegee Hardness, durometer	70
Squeegee Speed (not to exceed), cm/second	10
Squeegee pressure, initial, Kg	3
Snap-off, snap-off determined by PCB size, initial from 60 surface of substrate, mil	
Wet Film Thickness, μm	30 to 40
Cured Film Thickness, μm	10 to 14
Screen Emulsion Thickness:	
Laminate, direct capillary film, μm	38
Build-up, direct coated emulsion, μm	12

TYPICAL DRYING CYCLE

5 to 10 minutes @ 80 °C, if co-curing different resistors

TYPICAL CURING PERFORMANCE

Percent Volatiles

VOC, g/l 578

Convection Box Oven

30 minutes @ 120°C

Infrared Heat Source

2 minutes @ 250°C

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

After application

Electrical Properties

Resistivity, cured thickness of 18 to 24 μm, ±10%, ohms/sq:	
M 3010-1RS	10
M 3012-1RS	100
M 3013-1RS	1,000
M 3014-1RS	10,000
M 3015-1RS	100,000
M 3021-1RS	20

Power Rating:

Watts/in ² , Aluminum backed, max	10
Watts/cm ² , Aluminum backed, max	1.8
Resistivity change after humidity test	10
100 ohm/sq to 1 meg ohm/sq, max, %	
Resistivity change after thermal aging	10
1000 hours @ 80°C on Polyester, max, %	
Temperature Coefficient of Resistance (TCR), on FR4 600, ppm	

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

1. Should thinning become necessary, use carbitol acetate (2 % by weight).
2. Use standard screen cleaners for cleanup. Recommend ICC Cleaner #857 followed by a propanal wipe.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Store in a cool, well ventilated area.

Optimal Storage : 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{psi} \times 145 = \text{N/mm}^2$

$\text{MPa} = \text{N/mm}^2$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1