

LOCTITE® PC 9021 APAC

September 2011

PRODUCT DESCRIPTION

LOCTITE® PC 9021 APAC provides the following product characteristics:

| | |
|--|--|
| Technology | Epoxy |
| Chemical Type | Epoxy |
| Appearance (Resin) | Light beige liquid ^{LMS} |
| Appearance (Hardener) | Blue translucent liquid ^{LMS} |
| Appearance (Mixture) | Bluish green to dark grey ^{LMS} |
| Components | Two components - requires mixing |
| Mix Ratio, (by volume) Resin : Hardener | 8.55 : 1 |
| Mix Ratio, by weight - Resin : Hardener | 100 : 6.5 |
| Cure | Room temperature cure |
| Application | Crusher repair products |

LOCTITE® PC 9021 APAC is the original 100 % solids epoxy system for backing wear metal in crushers and grinding mills. The product needs no melting or special equipment and has high volumetric stability that eliminates formation of gaps between backing and liners or support structures. It is easy and safe to use.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Resin:

| | |
|--|---------------------------------|
| Weight Per Gallon, lbs/gal | 14.7 to 15.2 |
| Viscosity, Brookfield - RV, 25°C, mPa·s (cP): Spindle 6, speed 20 rpm | 20,000 to 38,000 ^{LMS} |

Hardener:

| | |
|--------------------------|-----------------------------|
| Specific Gravity @ 25 °C | 0.97 to 1.02 ^{LMS} |
|--------------------------|-----------------------------|

Mixed Properties:

| | |
|----------|---|
| Coverage | 5,576 cm ³ per 7.5 liter kit (340 in ³ per 2 gallon kit) |
|----------|---|

TYPICAL CURING PERFORMANCE

Curing Properties

| | |
|--|-------------------------|
| Gel Time @ 25 °C, minutes: 400 g mass | 14 to 22 ^{LMS} |
| Working Time @ 25 °C, minutes | 10 |
| Cure Time @ 25 °C, hours | 8 |

TYPICAL PROPERTIES OF CURED MATERIAL

Cured @ 25 °C

Physical Properties:

| | |
|--------------------------------------|---|
| Shore Hardness, ISO 868, Durometer D | 90 |
| Compressive Strength, ISO 604 | N/mm ² 106.9 (psi) (15,500) |

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for use

Preparation of Metallic Parts

- All metallic parts that come in contact with LOCTITE® PC 9021 APAC should be free of rust, dirt, grease and oil. Seal hook holes and bottom joints, and protect threaded parts of shafts where necessary. To facilitate easier removal of worn liners, coat crusher heads and mill shells with grease.

Preparation of Backing Material

- LOCTITE® PC 9021 APAC must be at 15 °C to 26 °C before use. Lower temperatures give longer working life, but higher viscosity (harder to pour), while higher temperatures reduces working time to pour into crusher.

Mixing:

- Pre-mix resin approximately 1 minute.
- Shake hardener thoroughly mixing its contents.
- While mixing resin, add hardener contents.

Application

- Pour mixture immediately after mixing. Pour at one place and allow LOCTITE® PC 9021 APAC to fill the cavity and push out the air in front of it. Use dam (tin, cardboard, clay, etc.) to direct the flow when necessary. Unmixed resin (different color clinging to the sides and bottom) should not be drained into the crusher.
- Succeeding kits may be mixed and poured individually as needed. LOCTITE® PC 9021 APAC adheres to itself.

Caution: Use an approved, positive-pressure, supplied air respirator when welding or torch cutting near cured compound. **Do Not** use open flame on compound.

Technical Tips for Working With Epoxies

Working time and cure depends on temperature and mass:

- The higher the temperature, the faster the cure.
- The larger the mass of material, the faster the cure.

To speed the cure of epoxies at low temperatures:

- Store epoxy at room temperature.
- Pre-heat repair surface until warm to the touch.

To slow the cure of epoxies at high temperatures:

- Mix epoxy in small masses to prevent rapid curing.
- Cool resin/hardener component(s).

Loctite Material Specification^{LMS}

LMS dated January 23, 2002 (Resin) and LMS dated June 13, 2001 (Hardener). Test reports for each batch are available for the indicated properties. LMS test reports include selected QC

test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Loctite Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\mu\text{m} / 25.4 = \text{mil}$

$\text{N} \times 0.225 = \text{lb}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{N/mm}^2 \times 145 = \text{psi}$

$\text{MPa} \times 145 = \text{psi}$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1