



# LOCTITE® PU EV 9790

May 2025

**Product description**

LOCTITE® PU EV 9790 provides the following product characteristics:

Technology	2C polyurethane gasket adhesive
Chemical type	Polyurethane
Appearance (uncured)	Black
Components	Two-component – requires no external mixing
Viscosity	Paste
Cure	Two-component
Application	EV battery housing gasketing
Environmental temperature at application	5 to 45°C
Material application temperature	60 to 70°C
In service temperature	-40 to 80°C
Short exposure (up to 1 hr)	120°C
Specific benefits	<ul style="list-style-type: none"><li>• Fast sealing performance</li><li>• Moisture independent curing</li><li>• Rapid and precise application</li></ul>

LOCTITE® PU EV 9790 is a two-component polyurethane housing sealant. This system enables consistent curing in lower temperatures and lower humidity environments. It cures independently from environmental conditions by using a B-component which will be mixed automatically to the A-component during application.

LOCTITE® PU EV 9790 is suitable for EV battery housing sealing against steel (with primer/activator), aluminum or various types of composites (e.g. sheet molding composites based on carbon fibers and glass fibers) found in today's assemblies.

**Typical properties of uncured material**

**As dispensed**

Specific gravity @ 23°C ~1.2

**Typical curing performance**

Work time @23°C (from material application until housing assembly) ~25

**Typical performance of cured material**

Cured for 7 days @ 23 °C, 50% RH

**Physical properties**

Hardness, Durometer A DIN53505	~60
Elongation at break, % DIN53505	~370
Tensile strength, N/mm <sup>2</sup> DIN53505	~8.5

**GENERAL INFORMATION**

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet.

**Direction for use**

**Important**

For application of primers, fillers, primer fillers, paints or other coatings, technical guidelines from manufacturers have to be considered and followed.

**Pre-treatment**

1. The substrate to be bonded must be dry and free from oil, dust, grease, and other contaminations.
2. Check the flange for damage or scratches and make sure it fits.
3. To obtain an optimal adhesion on the new battery cover flanges (or one without previous sealant adhered) we recommend TEROSON® VR 10 or TEROSON® SF 7063.

Solvent-based cleaning process:

- Wipe off surface with a lint free cloth and TEROSON® VR 10 .
- Abrade bond line with a smooth abrasive pad or wetted TEROSON® BOND SPONGE
- Wipe off surface again with a lint-free cloth and TEROSON® VR 10 and let dry approximately 5 minutes.



## Priming

1. Before opening the TEROSON® BOND ALL-IN-ONE PRIMER bottle, shake well (at least 1 minute).
2. Apply primer with wool dauber in one pass on the bond line (allow to flash off for 2 minutes).
3. Within the first 2 hours after cutting back the old adhesive bead in the body frame, it does not need to be primed. But if the replacement takes longer than 2 hours, the old cut bead needs to be activated with TEROSON® BOND ALL-IN-ONE PRIMER. NOTE: Provided that it is not contaminated with dust or grease, the old cut adhesive bead is the best adhesive surface for the LOCTITE® PU EV 9780 adhesive.
4. If battery housings are bonded which have been pre-coated with a primer or PU-based adhesive/sealant, TEROSON® BOND ALL-IN-ONE PRIMER is also suitable to ensure the correct adherence of LOCTITE® PU EV 9790 to the pre-coating.
5. Using a wool dauber, a thin layer of TEROSON® BOND ALL-IN-ONE PRIMER is applied to the pre-coating. Allow to flash off for 2 minutes. Subsequently, TEROSON® PU EV 9780 is applied as usual, but taking into consideration the layer thickness of the pre-coating.

## Application

1. The EV Battery housing gasketing adhesive LOCTITE® PU EV 9790 is best applied from cartridges using commercial equipment such as hand, battery driven or air-pressure dispensers with a piston rod.
2. Prior to its use, the cartridge of LOCTITE® PU EV 9790 must be warmed to above 60°C if the ambient temperature is too low making it difficult to dispense the adhesive. There are 2 heating devices which could be used. In the TEROSON® ET CR HEATING BOX 2PC minimum 30 minutes or in the TEROSON® ET CR FC HEATINGBOX device minimum 60 minutes.
3. After piercing the top membrane, the B-component has to be screwed on the cartridge thread and application must be started immediately.
4. For application, we recommend using the dispenser TEROSON® POWERLINE II. Make sure to adjust the working pressure to 9 to 11 bar effective at the cartridge piston!
5. Application should be performed ideally in one continuous bead, if possible.

## Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal storage: 15°C to 25°C. Storage below 5°C or greater than 25°C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

## Product specification

The technical data contained herein are intended as reference only and are not considered specifications for the product. Product specifications are located on the Certificate of Analysis or please contact Henkel representative.

## Approval and Certificate

Please contact Henkel representative for related approval or certificate of this product.

## Data ranges

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23°C / 50% RH = 23±2°C / 50±5% RH

## Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\mu\text{m} / 25.4 = \text{mil}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{N/mm}^2 \times 145 = \text{psi}$   
 $\text{MPa} \times 145 = \text{psi}$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$



**Disclaimer**

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

## Reference 1