

# LOCTITE® SI 5045™

Known as LOCTITE® 5045™  
November 2020

## PRODUCT DESCRIPTION

LOCTITE® SI 5045™ provides the following product characteristics:

<b>Technology</b>	Silicone
<b>Chemical Type</b>	Alkoxy silicone
<b>Appearance (uncured)</b>	Translucent paste
<b>Components</b>	One component - requires no mixing
<b>Viscosity</b>	Paste
<b>Cure</b>	Room temperature vulcanizing (RTV)
<b>Application</b>	Bonding, Sealing, or Coating
<b>Specific Benefits</b>	<ul style="list-style-type: none"> <li>Non-corrosive</li> <li>Enhances load bearing and shock absorbing characteristics of the bond area</li> <li>High Strength</li> </ul>

LOCTITE® SI 5045™ is a one component RT cure silicone product designed for bonding, sealing, and coating of components especially for the military, automotive and industrial markets. The non-slumping nature of this product makes it ideal for reinforcing and strain relieving delicate components. LOCTITE® SI 5045™ resists weathering, moisture, ozone and retains its properties through severe environments. This product is typically used in applications up to 200 °C (392°F).

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 23 °C	1.14
Solids/Non-Volatile Content, %	92
Extrusion Rate, g/min, Pressure 0.62 Mpa, 15 seconds @ 25°C Semco Cartridge	40

## TYPICAL CURING PERFORMANCE

### Tack Free Time

Tack Free time is defined as the time required to achieve a tack free surface.

Tack Free Time, hours	5
Cured @ 23 °C / 50% RH	

## TYPICAL PERFORMANCE OF CURED MATERIAL

Cured for 1 week @ 23°C / 50% RH

## Physical Properties:

Coefficient of Thermal Expansion, ISO 11359-2, K <sup>-1</sup>	3×10 <sup>-4</sup>
Coefficient of Thermal Conductivity, ASTM E 1225, W/(m·K)	0.2
Water Vapor Trans. Rate, ASTM E96, g/(h·m <sup>2</sup> )	0.48
Water Absorption, ISO 62, % 24 hours in water @ 23°C	0.01
Shore Hardness, ISO 868, Durometer A	25
Elongation, at break, ISO 37, %	500
Tensile Strength, ISO 37	N/mm <sup>2</sup> 3 (psi) (430)
Tear Strength, ISO 34-1, Die B	N/mm 40 (lb/in) (230)

## Electrical Properties:

Dielectric Breakdown Strength, IEC 60243-1, kV/mm	18
Volume Resistivity, IEC 60093, ohm-cm	4×10 <sup>15</sup>
Dielectric Constant / Dissipation Factor, IEC 60250:	
100 Hz	3.0 / 0.006
1 MHz	3.1 / 0.01

## Adhesive Properties:

Peel Adhesion (pli method), ASTM D 903:	
Aluminum (primed)	N/mm 13 (lb/in) (75)
Steel (primed)	N/mm 8.7 (lb/in) (50)

## TYPICAL ENVIRONMENTAL RESISTANCE

### Heat Resistance

Cured for 1 week @ 200°C	
Shore Hardness, ISO 868, Durometer A	45
Elongation at break, ISO 37, %	330
Tensile Strength, ISO 37	N/mm <sup>2</sup> 3 (psi) (430)

### Hydrolytic Stability

Cured for 28 days @ 95°C / 98% RH	
Shore Hardness, ISO 868, Durometer A	29
Elongation at break, ISO 37, %	500
Tensile Strength, ISO 37	N/mm <sup>2</sup> 5 (psi) (730)

**GENERAL INFORMATION**

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

**Directions For Use:**

1. For best performance bond surfaces should be clean and free from grease.
2. Full performance properties will develop over 72 hours.
3. Moisture curing begins immediately after the product is exposed to the atmosphere, therefore parts to be assembled should be mated within a few minutes after the product is dispensed.
4. Excess material can be easily wiped away with non-polar solvents.

**Storage**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

**Product Specification**

The technical data contained herein are intended as reference only and are not considered specifications for the product. Product specifications are located on the Certificate of Analysis or please contact Henkel representative.

**Approval and Certificate**

Please contact your local Henkel representative for related approval or certificate of this product.

**Data Ranges**

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23 °C / 50% RH = 23±2 °C / 50±5% RH.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\mu\text{m} / 25.4 = \text{mil}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{N/mm}^2 \times 145 = \text{psi}$   
 $\text{MPa} \times 145 = \text{psi}$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

**Disclaimer**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect

of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation or Henkel Canada, Inc. the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

