

LOCTITE STYCAST EO 1058

September 2017

PRODUCT DESCRIPTION

LOCTITE STYCAST EO 1058 provides the following product characteristics:

Technology	Epoxy
Appearance	Black
Cure	Heat cure
Application	Potting and Encapsulating

LOCTITE STYCAST EO 1058 is a one component, epoxy compound that cures at 125°C. LOCTITE STYCAST EO 1058 provides excellent environmental and thermal protection to encapsulated parts. This product is especially suited for use in protecting sensors used in harsh environments such as automotive applications.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield - RVT, 25 °C, mPa·s (cP):	
Spindle 7, speed 20 rpm	50,000
Filler Content, %	62
Specific Gravity	1.65
Pot Life @ 25 °C, days	10
Shelf Life @ -40°C (from date of manufacture), days	213
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE

Gel Time

Gel @ 121°C, minutes 12

Recommended Cure

2 hours @ 140°C or
3 hours @ 125°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Glass Transition Temperature (T _g), °C	140
Coefficient of Linear Thermal Expansion:	
Alpha 1, ppm/°C	24
Hardness, Shore D	90
Tensile Modulus	N/mm ² 4,826 (psi) (700,000)
Flexural Modulus	N/mm ² 7,860 (psi) (1,140,000)
Thermal Conductivity, W/(m·K)	0.54
Moisture Absorption, 120 hrs PCT @ 15 psi, %	0.78
Elongation, %	1.96

Electrical Properties

Dielectric Constant / Dissipation Factor:

@ 25 °C:	
@ 1KHz	4.31/4.94×10 ⁻³
@ 10KHz	4.0/4.56×10 ⁻²
@ 100KHz	3.77/3.49×10 ⁻²
@ 100 °C:	
@ 1KHz	4.27/5.05×10 ⁻³
@ 10KHz	3.98/4.11×10 ⁻²
@ 100KHz	3.78/3.0×10 ⁻²

TYPICAL PERFORMANCE OF CURED MATERIAL

Miscellaneous

Flexural Strength	N/mm ² 83 (psi) (12,000)
Tensile Strength	N/mm ² 70 (psi) (10,000)

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

DIRECTIONS FOR USE

1. This product should not be exposed to ambient air for greater than 1 hour prior to cure. Excessive exposure to the moisture in the atmosphere will degrade the cured properties of the material, resulting in impaired thermal and environmental resistance.
2. This product contains fillers that may settle upon prolonged storage. Thoroughly remix before use if there is any indication of filler settle.
3. Store in sealed containers, do not expose uncured material to moisture. If containers are opened, blanket with dry nitrogen before resealing.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : -40 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions $(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$ $\text{kV/mm} \times 25.4 = \text{V/mil}$ $\text{mm} / 25.4 = \text{inches}$ $\text{N} \times 0.225 = \text{lb}$ $\text{N/mm} \times 5.71 = \text{lb/in}$ $\text{psi} \times 145 = \text{N/mm}^2$ $\text{MPa} = \text{N/mm}^2$ $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$ $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$ $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$ $\text{mPa}\cdot\text{s} = \text{cP}$ **Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 0.2

Americas
+1.888.943.6535

Europe
+32.1457.5611

Asia
+86.21.3898.4800

For the most direct access to local sales and technical support visit: www.henkel.com/electronics