

# LOCTITE STYCAST ES 1001

November 2016

## PRODUCT DESCRIPTION

LOCTITE STYCAST ES 1001 provides the following product characteristics:

<b>Technology</b>	Epoxy
Appearance - Part A	Black
Appearance - Part B	Tan
Appearance (cured)	Black
Components	Two components - requires mixing
Mix Ratio by volume: Part A: Part B	1 : 1
Mix Ratio by weight: Part A: Part B	100 : 87
<b>Cure</b>	Room temperature cure
<b>Application</b>	Potting and Encapsulating

LOCTITE STYCAST ES 1001 is a two-component casting system with excellent handling properties. This low cost, flexible system is filled with a non-abrasive filler for machine metering/dispensing. This material has good thermal shock resistance and low exotherm, making it suitable for encapsulation of various components and modules. LOCTITE STYCAST ES 1001 is a low viscosity material, making it suitable for impregnating applications with small tolerances.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

### Part A Properties

Density, @ 25 °C, g/cm <sup>3</sup>	1.82
Viscosity, Brookfield - RVF, cP: Spindle 6, speed 2 rpm	14,000
Filler Content, %	50

### Part B Properties

Density, @ 25 °C, g/cm <sup>3</sup>	1.64
Filler Content, %	55
Viscosity, Brookfield - RVF, cP: Spindle 3, speed 10 rpm	3,500

### Mixed Properties

Density, @ 25 °C, g/cm <sup>3</sup>	1.83
Filler Content, %	52
Peak Exotherm Temperature, °C: 200 g mass	42
Pot Life @ 25 °C, minutes: 200 g mass	60
500 g mass	58
1,000 g mass	47
Viscosity, Brookfield - RVF, cP: Spindle 4, speed 2 rpm	10,000

## TYPICAL CURING PERFORMANCE

### Recommended Curing Conditions

- 24 hours @ 25 °C (Recommended cure)
- 3 hours @ 60 °C (Alternate cure)

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties :

Glass Transition Temperature, °C	36
Coefficient of Thermal Expansion, ppm/°C: Pre Tg (Alpha 1)	74
Post Tg (Alpha 2)	180
Coefficient of Thermal Conductivity, W/(m-K)	0.293
Linear Shrinkage, %	0.007
Shore Hardness, Durometer D	75
24 Hour Water Moisture Absorption, %	1.1
Izod Impact Strength, N/mm of notch	0.05
Tensile Elongation, %	45
Tensile Strength, psi	1,400
Compressive Strength, psi	14,000

### Electrical Properties:

Dielectric Strength, 10 mil thickness, volts/mil	1,100
Volume Resistivity, ohm-cm	2×10 <sup>13</sup>
Volume Resistivity, ohm-cm @ 105°C	4×10 <sup>9</sup>
Surface Resistivity, ohms @ 25°C	1×10 <sup>14</sup>
Surface Resistivity, ohms @ 105°C	2×10 <sup>11</sup>
Dielectric Constant / Dissipation Factor @ 25°C: 100 Hz	5.7 / 0.12
1 kHz	4.9 / 0.007
10 kHz	4.4 / 0.063
Dielectric Constant / Dissipation Factor @ 105°C: 100 Hz	20.0 / 4.36
1 kHz	11.8 / 0.974
10 kHz	8.6 / 0.104

## GENERAL INFORMATION

**For safe handling information on this product, consult the Safety Data Sheet, (SDS).**

### Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

**Note:** Before using this product please purge approximately 30 ml. of material prior to application. Discard purged material in accordance with the Material Safety Data Sheet. A video instruction is available upon request.

**DIRECTIONS FOR USE**

LOCTITE STYCAST ES 1001 will settle upon storage, especially at temperatures exceeding 28°C. Storage at the lower end of the recommended range will help to minimize filler settling. LOCTITE STYCAST ES 1001 should be warmed to room temperature prior to use.

**STORAGE:**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 8°C to 28°C. Storage below 8°C or greater than 28°C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{psi} \times 145 = \text{N/mm}^2$   
 $\text{MPa} = \text{N/mm}^2$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

**Disclaimer****Note**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel, is therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in

relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

## Reference 2

Americas  
+1.888.943.6535

Europe  
+32.1457.5611

Asia  
+86.21.3898.4800

**For the most direct access to local sales and technical support visit: [www.henkel.com/electronics](http://www.henkel.com/electronics)**