



LOCTITE SUPERGLUE Tube - CA Gel

LOCTITE SUPERGLUE-3 Power Gel

CHARACTERISTICS

LOCTITE® SUPERGLUE-3 Power Gel is a one-part instant liquid gel adhesive. It is designed for home-use and forms strong bonds between a wide range of common materials. The non-drip formula can be used on vertical or overhead surfaces. It is the ideal adhesive for bonding materials such as plastics, rubbers, metals, woods, ceramics, leather, fabrics, cardboard and paper.

LOCTITE® SUPERGLUE-3 Power Gel is resistant to shocks and is perfect for applications where some flexibility is required. The product has been formulated to allow some repositioning time when making the bond. Power Flex conforms to the EN204 D3 standard for wood adhesives making it water resistant but not suitable for continuous exposure to moisture.

Bonding Speed: Initial adhesion in 10 to 30 seconds, depending on the substrate.

Bond Strengths (ISO 4587): 15 to 25 N/mm² (tensile shear) in 12 to 24 hours, depending on the substrate. It is water-resistant to EN204-D3 standard and ceramic bonds can withstand >50 dishwasher cycles (under controlled laboratory conditions).



INSTRUCTIONS FOR USE

1. Ensure all surfaces to be bonded are clean and dry and close-fitting.
2. Avoid skin contact with the glue.
3. Apply a minimum quantity of LOCTITE® SUPERGLUE-3 Power Gel to one of the surfaces to be bonded.
4. Bring parts together immediately and hold by hand pressure for at least 1 minute.
5. Leave undisturbed for 10 minutes or preferably overnight to allow full bond strength to develop.
6. Avoid spillages and protect work surfaces. Remove cured residues of Glass Bond with LOCTITE® Super Glue Remover.
7. For best results, the bonds should be prepared at room temperature (15-30°C) and a minimum 30% relative humidity.
8. For optimum product life, wipe the nozzle with a tissue to remove excess adhesive, replace cap and store the pack in a cool, dry place.

TECHNICAL DATA

Composition	Ethyl cyanoacrylate
Appearance	Clear gel
Density, g/cm ³ @ 20°C	1.1
Viscosity,	non-drip Gel
Pack	3g tube
Safety	See SDS 1081573
Shelf life at 2 - 8 °C, months, unopened	24

LIMITATIONS

- Do not use on dusty, dirty or wet surfaces.
- Not suitable for bonding polypropylene, polyethylene, PTFE, silicone rubber, glass, glazed surfaces, very soft leather or foams.
- Never use for bonding assemblies that will hold hot liquids.
- Optimum bonding performance is achieved in dry conditions.

Storage

Store in a cool, dry place, out of reach of children.

HEALTH AND SAFETY

Before using the product please see related Material Safety Data Sheet that is available on request.



DISPOSAL

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.