

LOCTITE® TCF 14001

April 2025

PRODUCT DESCRIPTION

 $\mathsf{LOCTITE}^{@}$ TCF 14001 is a thermally conductive, two-part liquid Gap Filler material.

Technology	Silicone
Appearance - Part A	Red
Appearance - Part B	Yellow
Appearance (cured)	Brown
Cure	Room temperature cure or Heat cure
Application	Thermal management, Gap filler (2K)
Mix Ratio by weight: Part A : Part B	1:1
Mix ratio by volume: Part A: Part B	1:1
Operating temperature range	-40 to 200°C
Specific benefits	 High thermal conductivity Low thermal impedance High gap deflection tolerance Excellent ageing performance Stable interface adhesion Low modulus

LOCTITE® TCF 14001 is a two-component, silicone based, liquid gap filling material. The mixed material will cure at room temperature and can be accelerated with addition of heat. This liquid dispensed material offers infinite thickness variation and impart little to no stress on sensitive components during assembly. Once cured, it forms stable adhesion between interfaces.

Features and benefits

- Thermal conductivity: ≥14 W/m-K
- Dispensable liquid, 2K Silicone based Gap Filler
- Room temperature cure no oven required
- High gap stability
- · High sedimentation resistance and storage stability

Typical applications

- Telecom / Datacom / Power / Automotive
- Applications requiring high thermal transfer and low compressive stress

TYPICAL UNCURED PROPERTIES

LOCTITE® TCF 14001 Part A

Dispense rate, grams/minute

EFD 30cc syringe without needle, 90psi

Shelf life, days

180

LOCTITE® TCF 14001 Part B

Dispense rate, grams/minute

EFD 30cc syringe without needle, 90psi

Shelf life, days

180

Mixed properties

Dispense rate, grams/minute

EFD 50cc syringe with 17 mixing, 90psi

1.7

Pot life @ 25°C, hours

3

TYPICAL CURE SCHEDULE

Cure schedule for handling stability

hours @ 25°C 24 hours @ 85°C 2

The above cure profile(s) are guideline recommendations. These cure conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Hardness, Shore ou, 6 mm thick sample	62
Heat capacity, ASTM E1269, J/g-K	0.6
Density, g/cc	3.1
Siloxane content, ΣD3-D10, ppm	<100

Electrical properties

Dielectric constant, ASTM D150 @ 1000Hz 6.6Volume resistivity, ASTM D257, ohm-meter 8.6×10^9 Dielectric strength, ASTM D149, KV/mm 13

Thermal properties

Thermal conductivity, W/m-K
ASTM D5470, LW-9389
14.5
Thermal impedance @1mm, °C-cm²/K
ASTM D5470, LW-9389
0.76

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Configurations available

LOCTITE® TCF 14001 is available in the following configurations:

Cartridges 280 cc



Shipping conditions

Shipping conditions should be controlled between 5 to 35°C, non-frozen ambient.

Storage

Store product in an unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal storage: 5 to 35°C

Material removed from the package may be contaminated during use. Do not return product to the original package. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on the specifications of this product.

Approval and certificate

Please contact Henkel representative for related approval or certificate of this product

Data ranges

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23°C / 50% RH = 23 \pm 2°C / 50 \pm 5% RH

Conversions

 $(^{\circ}C \times 1.8) + 32 = ^{\circ}F$ $kV/mm \times 25.4 = V/mil$ mm / 25.4 = inches $\mu m / 25.4 = mil$ $N \times 0.225 = lb$ $N/mm \times 5.71 = lb/in$ $N/mm^2 \times 145 = psi$ $MPa \times 145 = psi$ $N \cdot m \times 8.851 = lb \cdot in$ $N \cdot m \times 0.738 = lb \cdot ft$ $N \cdot mm \times 0.142 = oz \cdot in$ $m \cdot m \times 0.142 = oz \cdot in$

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in Technical data sheet or any other written or recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 2

For the most direct access to local sales and technical support visit: https://www.henkel-adhesives.com