

# LOCTITE TCP 4000 PE

Known as PSX-Pe  
March 2015**PRODUCT DESCRIPTION**

LOCTITE TCP 4000 PE provides the following product characteristics:

<b>Technology</b>	Phase Change Thermal Interface Material
Appearance	gray
Phase change temperature	45 °C
Application Method	Stencil, Screen print or Manually apply
Typical Assembly Applications	Microprocessors, GPUs, Multichip modules, ASICs, IGBT, FBDIMM/Memory, Lidded processor applications and Active heat sinks in electronic applications
<b>Application</b>	Thermal management

LOCTITE TCP 4000 PE Extended Dry phase change material suitable for use between heat generating devices and the surfaces to which they are mounted or other heat dissipating surfaces. This material offers enhanced performance and reliability with the application ease of thermal grease. LOCTITE TCP 4000 PE is supplied in cartridges. Other packaging formats are available upon request.

**TYPICAL PROPERTIES**

Shelf Life @ 25°C, months ≥6

**Printed Material:**

Casson Base Viscosity @ 25 °C, mPa·s (cP):  
Haake 550, PK1, 1° :  
@ 1 rpm 200,000  
@ 10 rpm 80,000  
Specific Gravity 1.8

**Solid Material:**

Specific Gravity 2.0  
Thermal Conductivity, W/(m·K) 3.4

**TYPICAL DRYING PERFORMANCE****Recommended Drying Conditions**

@ 0.051 mm Thickness:  
4 hours @ 60°C or  
7 minutes @ 125°C

@ 0.152 mm Thickness:  
11.5 hours @ 60°C or  
12 minutes @ 125°C

@ 0.254 mm Thickness:  
18.5 hours @ 60°C or  
18 minutes @ 125°C

Drying at 22°C is not recommended for &gt;500 hours.

The above drying profile is a guideline recommendation. Conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer drying equipment, oven loading and actual oven temperatures.

**GENERAL INFORMATION**

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

**DIRECTIONS FOR USE**

1. Once the compound is applied, it will dry to a solid phase change material. Drying is required for optimal thermal performance.
2. The material flows at the phase change temperature and conforms to the surface features of the heat sink and component.
3. Upon flow, air is expelled from the interface, reducing thermal impedance and the material performs as a highly efficient thermal transfer material.

**Application:**

Jars / Screens

1. Keep jars closed tightly when not in use. Open jars will evaporate solvent affecting the performance of the material.
2. Place a small amount of material onto the screen. With the substrate under the screen, draw the material down, applying the material onto the substrate.
3. Recommended maximum thickness is 10 mils (254 microns) to ensure complete drying under normal conditions.

Syringe Dispense

1. Use a hand syringe or time pressure dispenser. Dispense the required amount of material onto the substrate.
2. Ideal performance is achieved by having a thin layer of material. Therefore the LOCTITE TCP 4000 PE material should be drawn down or smoothed out to provide a thin layer.
3. Recommended maximum thickness is 10 mils (254 microns) to ensure complete drying under normal conditions.

**STORAGE:**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: Below 27°C. Storage greater than 27°C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Not for product specifications**

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

**Conversions**
 $(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$ 
 $\text{kV/mm} \times 25.4 = \text{V/mil}$ 
 $\text{mm} / 25.4 = \text{inches}$ 
 $\text{N} \times 0.225 = \text{lb}$ 
 $\text{N/mm} \times 5.71 = \text{lb/in}$ 
 $\text{psi} \times 145 = \text{N/mm}^2$ 
 $\text{MPa} = \text{N/mm}^2$ 
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$ 
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$ 
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$ 
 $\text{mPa}\cdot\text{s} = \text{cP}$ 
**Disclaimer****Note**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel, is therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a**

**particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1