

THREADLOCKER BLUE 242[®]

DESCRIPTION

LOCTITE[®] THREADLOCKER BLUE 242[®] is designed for the locking and sealing of threaded metal fasteners which require normal disassembly with standard hand tools. The product cures anaerobically, when there is an absence of air between close fitting metal surfaces. Loctite Threadlocker Blue 242 is particularly suited for applications on less active substrates such as stainless steel and plated surfaces.

Available As:

Item #	Country	Package	Size
209728	USA	Plastic carded squeeze tube	0.20 fluid ounce (6 mL)
2872401	USA	Paper carded squeeze tube	0.20 fluid ounce (6 mL)
303379	Canada	Plastic carded squeeze tube	0.20 fluid ounce (6 mL)

FEATURES & BENEFITS

- Medium strength can be removed with hand tools
- Prevents loosening of metal fasteners caused by shock and vibration
- Protects and seals threads from rust and corrosion

RECOMMENDED FOR

Use on metal fasteners 1/4" (6 mm) to 3/4" (19mm) in diameter in a wide variety of applications including:

Automotive – Valve covers, water pumps, alternators, oil pans

Maintenance – Light machinery, light conveyors, door hardware, tow motors

Home – Lawn Mowers, grills, locksets, bicycles

LIMITATIONS

- Not for use on plastic parts, particularly thermoplastic materials where stress cracking of the plastic could result.
- Not for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.
- A primer is needed if two inactive metals are used i.e., plated parts, black oxide coated.
- Do not use in applications requiring "food safe" locking and sealing of fasteners.
- When used in devices handling gasoline, petroleum oils, and natural gas, pressure should not exceed over 300 PSIG; devices holding butane and propane not to exceed 2-inch pipe size.

TECHNICAL DATA

Typical Uncured Physical Properties:

Color:	Blue	Odor:	Mild	
Appearance:	Liquid	VOC Content:	0.56% by weight	CARB
Base:	Dimethacrylate ester		6.17 g/L	SCAQMD
Viscosity:	800 – 1600 cps	Flash Point:	>212°F (>100°C)	
Specific Gravity:	1.10			

TECHNICAL DATA

Typical Application Properties:

Application Temperature: Apply above 50°F (10°C)	Lot Code 1BAA2230
Set Time: 10 minutes for active metals (steel) Longer for less active metals	Explanation: 1=Last digit of the year of manufacture
Cure Time: 24* hours	B = Month of Year (A=Jan, B=Feb., etc.)
Shelf Life: 24 months from date of manufacture (unopened)	Example: 1B = February 2021

*Time is dependent on temperature, humidity and thickness of adhesive applied

Typical Cured Performance Properties:

Color: Blue	Cured Form: Non-flammable, hard solid
Service Temperature: -65°F (-54°C) to 300°F (149°C)	Moisture Resistant: Yes

Adhesive Properties:

After 1 hour @ 72°F (22°C): Breakaway Torque: 3/8 x 16 steel nuts (grade 2) and bolts (grade 5)	50 to 150 lb-in (5.6 to 17 N·m)
Prevail Torque: 3/8 x 16 steel nuts (grade 2) and bolts (grade 5)	15 to 60 lb-in (1.7 to 6.8 N·m)
After 24 hours @ 72°F (22°C): Breakaway Torque (ISO 10964): 3/8 X 16 steel nuts (grade 2) and bolts (grade 5) 3/8 x 16 cadmium nuts and bolts 3/8 x 16 zinc nuts and bolts M10 black oxide steel nuts and bolts	70 to 150 lb-in (7.9 to 17 N·m) 10 to 60 lb-in (1.1 to 6.8 N·m) 20 to 60 lb-in (2.3 to 6.8 N·m) 71 to 168 lb-in (8 to 19 N·m)
Applicable Specifications: Tested to the requirements of	<ul style="list-style-type: none"> Military Specification Mil-S-46163A ASTM D5363

Chemical/Solvent Resistance: Aged under conditions indicated and tested @ 72°F (22°C)

Environment	°F/°C	% of Initial Strength		
		100 hours	500 hours	1000 hours
Motor oil (MIL-L-46152)	257/125	100	100	100
Unleaded gasoline	72/22	100	100	95
Leaded Gasoline	72/22	100	100	100
Brake fluid	72/22	100	100	100
Ethanol	72/22	100	100	95
Acetone	72/22	100	100	85
1,1,1 Trichloroethane	72/22	80	75	90
Water/ glycol 50/50	189/87		105	70

DIRECTIONS

Tools Typically Required:

Wear gloves and wash hands after use. Utility knife and damp cloth.

Safety Precautions:

Keep out of reach of children!

Preparation:

Protect work area. Parts to be sealed must be clean and dry. Shake product thoroughly before use. Unscrew cap and cut tip.

Note: To prevent the product from clogging in the nozzle, avoid touching the tube tip to the metal surface.

Application:

For Thru Holes:

Apply several drops of the product onto the bolt at the nut engagement area.

For Blind Holes:

Apply several drops of the product down the internal threads to the bottom of the hole.

For Sealing Applications:

Apply a 360° bead of product to the leading threads of the male fitting, leaving the first thread free. Force the material into the threads to thoroughly fill the voids. For bigger threads and voids, adjust product amount accordingly and apply a 360° bead of product on the female threads also.

Assemble parts and tighten as required. Sets in approximately 10 minutes and fully cures in 24 hours.

For Disassembly:

Remove with standard hand tools. In rare instances where hand tools do not work because of excessive engagement length, apply localized heat to nut or bolt to approximately 482°F (250°C). Disassemble while hot.

Clean-up:

Uncured: Wipe with a damp cloth.

Cured: Remove with a combination of soaking in a LOCTITE solvent (such as SF 790 Chisel Paint Stripper or Loctite 7601 Equipment Flushing Solvent) and mechanical abrasion such as a wire brush.

STORAGE & DISPOSAL

NOT DAMAGED BY FREEZING. Close the tube tightly after each use. Store product in the unopened container in a dry location. Optimal storage is between 46°F (8°C) to 70°F (21°C).

LABEL PRECAUTIONS

WARNING: Contains methacrylate ester. IRRITANT. May cause allergic skin reaction and eye irritation. Avoid eye and skin contact. Avoid breathing vapors. Use only with adequate ventilation.

FIRST AID: For eye contact, flush with water for 15 minutes; call a physician. For skin contact, wash thoroughly with soap and water. If inhaled, move to fresh air. If swallowed, call Poison Control Center or doctor immediately. Do not induce vomiting. Obtain medical attention. **KEEP OUT OF REACH OF CHILDREN**



WARNING: Cancer and Reproductive harm – www.P65Warnings.ca.gov

Refer to the Safety Data Sheet (SDS) for further information.

DISCLAIMER

The information and recommendations contained herein are based on our research and are believed to be accurate, but no warranty, express or implied, is made or should be inferred. Henkel recommends purchasers/users should test the products to determine acceptable quality and suitability for the intended use. All adhesive/sealant applications should be tested under simulated or actual end use conditions to ensure the adhesive/sealant meets or exceeds all required project specifications. Since assembly conditions may be critical to adhesive/sealant performance, it is also recommended that testing be performed on specimens assembled under simulated or actual production conditions. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement, or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

LIMITED WARRANTY

This product is warranted by Henkel Corporation to be free from defects in materials when used as directed. Henkel's sole obligation shall be, at its option, to replace or refund the purchase price of product proven to be defective. Henkel makes no other warranty – express or implied – including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE and will not be liable for consequential or incidental damages. This Limited Warranty gives you specific legal rights, which vary from state to state. For warranty assistance, contact Henkel at 1.800.624.7767 M-F 9:00 am to 4:00 pm ET



Trusted Performance. Proven Results.

For over 50 years, LOCITE Brand adhesives and sealants have taken on the toughest jobs. Used in race cars, airplanes, and even in the space-shuttle, LOCITE provides solutions for the most demanding industrial, professional and consumer applications. LOCITE gives you the specialization, power, and performance to not only get your job done, but to get it done right.

For Technical Assistance call : 1-800-624-7767 – Mon-Fri - 9:00a – 4:00p ET
www.loctiteproducts.com



LOCTITE Brand is part of the Henkel family of brands. Founded in 1876, Henkel is a global leader in the consumer and industrial businesses. Henkel operates worldwide with leading brands and technologies in three business areas: Laundry & Home Care, Beauty Care (Consumer Brands) and Adhesive Technologies.

Henkel Corporation - Professional & Consumer Adhesives Headquarters - Rocky Hill, CT 06067
www.henkelna.com