

# LOCTITE UK 8119 B1 / LOCTITE UK 5400

January 2014

## PRODUCT DESCRIPTION

LOCTITE UK 8119 B1 / LOCTITE UK 5400 provides the following product characteristics:

<b>Technology</b>	Polyurethane
<b>Product Type</b>	Casting Resin
<b>Cure</b>	Polyaddition
<b>Condition</b>	Solvent-free
<b>Components</b>	Two-components
<b>Component A</b>	Resin
<b>Component B</b>	Hardener
<b>Application</b>	Assembly
<b>Appearance (Comp. A)</b>	beige
<b>Appearance (Comp. B)</b>	brown
<b>Mixing Ratio, by weight Comp. A : Comp. B</b>	4 : 1
<b>Mixing Ratio, by volume Comp. A : Comp. B</b>	3 : 1

LOCTITE UK 8119 B1 / LOCTITE UK 5400 is a solvent-free two-component potting compound, based on polyurethane. The resin part (component A) contains organic compounds with hydroxyl groups, the hardener (component B) is based on isocyanates.

By mixing both components in a weight ratio of 4 : 1, a hard elastic product is formed through chemical reaction. After curing the product exhibits no measurable change in volume.

As natural raw materials (from different cultivation areas) are used a variation in color between different batches is possible.

## APPLICATION AREAS

LOCTITE UK 8119 B1 / LOCTITE UK 5400 is used as a potting material or casting resin particularly for the manufacture of industrial and automotive filters

The product shows a good behaviour against chemical agents and in particular automotive medias such like gazole, motor oils, and petrols.

The good impregnation of glass fibers, kevlar and nonwoven materials by LOCTITE UK 8119 B1 / LOCTITE UK 5400 allows to use it in manufacture of air, oil, diesel oil and petrol filters.

## TECHNICAL DATA

### Component A

#### Loctite UK 8119 B1:

Consistency:	liquid
Density, g/cm <sup>3</sup>	1.58 to 1.68
Viscosity, Brookfield - RVT, 20°C, mPas * Henkel method 10	4,000 to 6,000

### Component B

#### Loctite UK 5400:

Consistency:	thin liquid
Density, g/cm <sup>3</sup>	1.17 to 1.27
Viscosity, Brookfield - RVT, 20°C, mPas * Henkel method 10	250 to 350

### Mixture (Component A + B):

Consistency:	liquid
Viscosity, Brookfield - RVT, 25°C, mPa.s * Henkel method 11	2,000 to 4,000
Pot life (125g, 20 °C) , sec Henkel method 20	45 to 75
Tensile Shear Strength, MPa EN 1465 / Henkel method 40	>6
Shore hardness D, 20 °C	> 80D
Service Temperature, °C	- 40 to 80
Short exposure (1 h), °C	120

All technical data based on Henkel test method.  
Data with \* are specified.

## DIRECTIONS FOR USE

### Preliminary Statement:

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

### Pretreatment:

The substrate should be clean, dry, free of dust, oil, grease and other contaminants. The usage of suitable primers on metal surfaces can improve the adhesion and/or the long-term bond stability. The surface of plastic materials should be cleaned, so as to remove any kind of release agents present on the substrate surface. An improvement of the adhesion can be achieved by grinding or sandblasting the surface.

### Application:

Component A must be properly and slowly homogenized before use.

Components can be mixed manually by using an electrical hand mixer or by using a two-component dispensing system.

After mixing no streaks must be visible. The casting resin is only to be used within a limited time (pot life). After this time the mixture gels up and is not suitable for use. Therefore only the amount that can be applied within the time of pot life should be mixed. The pot life depends on the quantity and temperature of the mixed batch. With larger quantities and an increase in temperature, the pot life decreases. Lower temperatures extend the pot life. Components should not come into contact with moisture during storage or application. Contact with moisture (water vapour) generates foaming of the casting resin and weakens the bondline. Therefore all packaging should be sealed properly and protected against humidity during storage.

#### **Curing:**

LOCTITE UK 8119 B1 / LOCTITE UK 5400 can be cured at room temperature above 15°C and elevated temperatures (up to 60°C). The curing time can be reduced by increasing the temperature or the addition of the accelerator Loctite UK 6100, with the simultaneous reduction of processing time (i.e. pot life, open time) to be observed. While curing there should be adequate contact pressure (presses, clamps) and fixture hold the joint in place. An adhesive squeeze out along the bond line is a good indication of sufficient adhesive in the joints.

#### **Cleaning:**

Fresh, uncured material (cleaning application equipment, substrate contamination etc.) can be removed with LOCTITE SF 8040; cured adhesive can only be removed mechanically.

#### **Classification:**

Please refer to the corresponding **Material Safety Data Sheets** for details on:

**Hazardous Information**  
**Transport Regulations**  
**Safety Regulations**

#### **Storage**

##### **Component A**

Recommended Storage Temperature, °C	15 to 30
Shelf-life (in unopened original packaging)	6 months

##### **Component B**

Recommended Storage Temperature, °C	15 to 30
Shelf-life (in unopened original packaging)	12 months

## **ADDITIONAL INFORMATION**

### **Disclaimer**

#### **Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

#### **Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0