



Technical Data Sheet



Technical Data Sheet
Ref: NRPTX29000
Issued: 08/10/2025
Number of pages: 3

Pattex No More Nails Strong & Easy Tube & Easy Pulse



CHARACTERISTICS

- Solvent-free dispersion formula
- High initial tack – 250kg/m²*
- Mount without drilling or mechanical fixings
- Fast drying on absorbent surfaces
- High adhesion properties
- Rigid bonding
- Gap filling up to 10mm
- Over paintable once dry
- Minimum application temperature +10°C
- Repositionable for up to 15 minutes
- Low odour
- Interior use

* Henkel internal laboratory method: 25 g/cm²

APPLICATION FIELD

Pattex No More Nails Strong & Easy is suitable for bonding many materials, e.g. plaster, concrete, plaster board, gypsum boards, wood materials (e.g. chip boards), MDF and polyurethane rigid-foams, most plastics (except PE, PE, PTFE).

Ideal for fixing:

- Skirting boards made of wood and PVC
- Coving
- Wood
- Window ledges
- Coat hooks and many other internal bonding applications
- Pannelling and mouldings



INSTRUCTIONS FOR USE

Pretreatment


Ensure surfaces to be bonded are clean and free of dust, grease or oil.

One surface of the materials to be bonded must be absorbent to allow the adhesive to dry and to ensure a strong, secure bond.

To achieve a good bond on highly water-absorbent surfaces, moisten the surface with a spray bottle or wet brush before bonding. For two non-absorbent or water-sensitive surfaces, use other products (e.g. UniBond No More Nails Waterproof).

Application

Apply adhesive onto one of the surfaces: 1) In spots in order to smooth uneven surfaces, 2) in wave-like form for higher initial tack with wide surfaces or 3) in straight strands for smaller surfaces.



Application of the adhesive

Bonding of panels, plastic decoration details, acoustic panels etc.:

Place panel 1-2 cm off the area to be bonded, then slide into correct position and press firmly with a twisting action. Heavy or distorted items may need additional fixings or support whilst drying.

TECHNICAL DATA

Uncured product	
Base	Water-based dispersion
Odour	Characteristic
Application temperature	+10°C - +40°C (substrate and ambient)
Density (ISO 2811-1)	~ 1,35 g/cm ³
Open time	~ 30 minutes (23°C, 50% r.h.)
Initial tack	~ 24 - 28 g/cm ² (240-280kg/m ²)
Drying time	~ 24 h (depends on substrates and thickness)
Shelf Life	18 months From date of production if stored in unopened original cartridges, in dry conditions and protected from direct sunlight at temperatures between +5°C and 25°C.
Coverage:	One cartridge is sufficient for approx. 11 linear meters (for 5mm bead). Typical applications require 200-400g of adhesive per m ² .
Cured product	
Odour:	Odourless
Tensile shear strength (DIN EN 205)	~ 5-6 N/mm ² (lap-shear strength, wood/wood)
Tensile strength Fmax	~ 4 N/mm ² (DIN 53504)
Service temperature	-20°C - +70°C

LIMITATIONS

Only for interior use in dry service conditions

Not suitable for areas of constant immersion or permanent damp



Dries by water evaporation, so one of the surfaces to be bonded must be porous (absorbent)
Very heavy items may require support whilst drying or additional fixings
No adhesion to PE, PP, PTFE(Teflon®). Not recommended for natural stone (e.g. marble)
Not suitable for fixing mirrors

Cleaning

Immediately remove any adhesive residue with a damp cloth. Cured material can only be removed mechanically.

Storage

Store in cool dry conditions, protected from frost.

Packaging

Air Pulse pressurised container
PE tubes

HEALTH AND SAFETY

Before using the product please see related Material Safety Data Sheet that is available on request.

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

Henkel Norden AB

Box 1155, SE-172 23

Sundbyberg

SE: Tel. +46 10 480 75 00, DK: Tlf +45 4330 1300, NO: Tlf. +47 2337 1520, FI: Puh. +358 20 122 311

Consumer service

SE: Tel. 010 480 7601, DK: Tlf. 80 88 77 05, NO: Tlf. 800 191 00, FI: Puh. 0800 165 066

Consumerservice-ac.norden@henkel.com