



RUBSON

Acrylic A1

Technical Data Sheet v.3, April 2026

High performance one-part elastic acrylic sealant for movement joints.

CHARACTERISTICS


RUBSON Acrylic A1 is a one-part elastic joint sealant, based on an acrylic dispersion. RUBSON Acrylic A1 is a non-sag sealant for indoor and outdoor joints with high movement capability.

- Very high elasticity
- Compatible with all paints (see notes on application)
- Excellent ageing resistance
- Excellent compatibility with paints
- Easy to apply / very good application and tooling properties
- Good adhesion to many substrates without primer such as concrete, wood etc.
- Even bonds to damp, absorbent substrates without primer
- Virtually odorless
- Free from phthalate plasticizers
- High durability

APPLICATION FIELD

- Façade joint sealing
- Sealing of connection joints with high movements indoor and outdoor
- Sealing of wall joints and cracks including façade cracks
- Sealing of joints in light prefabrication elements
- For connection joints around window and door frames (wood, metal, PVC), windowsills, drywall constructions, ceilings, PVC-pipes/conduits etc.
- Finishing joints along baseboards, walls, partitions, stairs, beams and window frames
- Movement joints in facades
- Aerated concrete connection joints
- For sealing of connection joints on substrates such as plaster, concrete, aerated concrete, brick, plasterboard, aluminum, wood, PVC, etc.
- Applications indoors and outdoors

STANDARDS

Certification Label 	SNJF 12.5 P plastic sealant Façade n° 4850*
EN 15651-1 (CE marking)	Product type F-EXT-INT: sealant for facade for interior and exterior application
GEV EMICODE®	EC 1 PLUS (very low emissions)
Conforms to IVD-Instruction Sheet No. 9	
VOC emission class (France)	Class A+
* Reference documents and information relating to the SNJF Label available at www.oc-sjff.fr .	

INSTRUCTIONS FOR USE

The application of masonry joints (wall joints and cracks, light prefabrication joints, sealing before impermeability coatings...) is to be made according to DTU 44.1 and 42.1.

RUBSON Acrylic A1 is supplied ready to use and can be applied from the cartridge using a standard air or hand operated gun, with no special pre-treatment.

The joint width must be designed to suit the movement capability of the sealant.

- In general, the joint width should be > 10 mm and < 30 mm if movement is to be expected. A width to depth ratio of ~ 1:0.5 should be maintained.
- Recommended minimum joint width for joints around windows and doors: 10 mm
- For triangular joints the sides should be 6 mm minimum.

Joint preparation

The substrates to seal should be clean, dry and free of dust, oils, grease and loose particles. Porous substrates (e. g. concrete, plaster, wood...) should be wetted well before applying the sealant. Where necessary completely remove old sealant and other residues. Surfaces can be degreased with the appropriate cleaner. If needed, prime the substrate with an appropriate fixer before sealing. To achieve visually appealing joints, we recommend masking the joint edges with a suitable adhesive tape. After joint and substrate preparation, insert backing rod (closed cell, PE-foam backing rods) to required depth if necessary.



Application

Cut off the top of cartridge cap above the thread, screw on the plastic nozzle and cut at an angle to match the joint strand width required. Insert the cartridge into a sealant gun and inject sealant into the joint making sure that the sealant is in full contact with the sides of the joint and avoid air entrapment.

Tooling

Directly after application, the product should be tooled firmly against the joint sides to ensure good adhesion. The joint can be lightly sprayed with clean water before tooling. Remove the masking tape whilst the sealant has still not formed a skin and tool the joint to a smooth surface with water. Remove water residues and protect the surface of the sealant from water (rain) until a skin has formed.

Cleaning tools

Fresh, uncured product can be removed with water. Clean tools and application equipment with water immediately after use. Cured sealant is insoluble in all solvents and can only be removed mechanically (e.g. with knife).

TECHNICAL DATA

Uncured product

Chemical base	Acrylate dispersion, waterbased	
Odour	Characteristic	
Application temperature, (substrate and ambient), °C	+5 to +40	
Consistency	Non-slump paste	
Density, g/cm ³	~ 1.7 (white) ~ 1.6 (colors)	(ISO 2811-1)
Resistance to flow, mm	~ 0	(ISO 7390)
Skin formation time, minutes	~ 25	23°C, 50% r.h.
Curing speed, days/mm	~ 10/5	23°C, 50% r.h., bead 20x10 mm

Cured product

Odour	odorless	
Shore A hardness	~ 20	ISO 868
100% Modulus, N/mm ²	~ 0.1	ISO 8339-A
Elongation at break, %	~ 200	ISO 8339-A
Shrinkage, %	-22	ISO 10563
Movement capability, %	12.5	
Recommended joint width, mm	max. 30	
Service temperature, °C	-20 to +80	

LIMITATIONS

Sealants may only be painted over if the coating is able to follow the movements of the sealant (in general if joint movements are < 5%, depending on the coating) – otherwise cracks in the surface of the coating can occur. The product can be painted over with commercially available paint, varnish and glaze systems. Before use, pre-tests for paint compatibility and overpaintability are recommended.

RUBSON Acrylic A1 is early rain resistant. Short exposure to rain directly after application does usually not lead to a wash out of the undried sealant. Do not apply when rain or frost is imminent. Protect from rain after application for 1 hour minimum. During curing RUBSON Acrylic A1 must be protected from frost. After curing the product is waterproof and frost resistant.

Application during high temperature changes is not recommended (crack formation due to movements during the curing).

Do not use RUBSON Acrylic A1 as glazing sealant, in floor joints, on marble/natural stones, on bituminous substrates, natural rubber, chloroprene, EPDM or on building materials which might bleed oils, plasticizers or solvents which could attack the sealant. Do not use on easy corroding substrates like blank steel, iron etc.

Not suitable for joints with water pressure or joints with permanent water immersion (underwater systems, sanitary installations, flooring joints, balconies and terraces). Do not use RUBSON Acrylic A1 to seal bathtubs or washbasins.

Color deviations may occur e. g. due to exposure to chemicals or high temperatures. However, a change in colour does usually not affect adversely the technical performance or the durability.

For further information please contact the responsible sales representative.

GENERAL INFORMATION

Surfaces

The product is suitable for many types of construction materials: concrete, brick, fibre-concrete, painted metals, lacquered aluminum, anodized aluminum, wood, PVC etc. No adhesion to PE, PP, PTFE(Teflon®). Not recommended for marble, tile, ceramics. On plastics and paints the adhesion properties should be tested before use. In cases of unknown materials or critical applications adhesions tests are recommended or contact our Technical Service.

STORAGE

18 months from date of production if stored in unopened original cartridges, in dry conditions and protected from direct sunlight at temperatures between +10°C and 25°C.

Chemical resistance

The product is not recommended for applications with permanent contact with chemicals. Poor resistance to aromatic solvents, organic acids, concentrated alkalis and concentrated acids, chlorinated hydrocarbons, detergents. In cases of other chemicals contact our Technical Service.



HEALTH AND SAFETY

Before using the product please see related Safety Data Sheet that is available on request at 09 69 32 09 30 or on our website <https://mysds.henkel.com/index.html>.

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.