

TECHNOMELT® PUR 3317 BR

Known as Purmelt QR 3317 BR
September 2024

Product description

TECHNOMELT® PUR 3317 BR provides the following product characteristics:

Technology	Hotmelt
Product type	Reactive prepolymer
Application	Graphic industry
Cure	Moisture cure
Appearance	white, transparent, fluorescent

Application areas

- Perfect binding
- Book spine glueing of thread stitched books

Product properties

TECHNOMELT® PUR 3317 BR shows an excellent adhesion to a variety of papers and materials and is as well suitable for difficult-to-bond papers.

Depending on external conditions, 50 - 80% of the final bonding strength can be achieved already after 12 to 24 hours.

The adhesive cures to its final bond strength within 1 to 2 days - depending on the atmospheric humidity, the moisture content of the paper, the thickness of the adhesive film, the permeability of the material to be bonded and the storage temperature. After the physical curing process, however, the bonded product can already be processed.

The storage temperature of freshly binded products should not be below 18 °C as otherwise the reaction time of TECHNOMELT® PUR 3317 BR will be significantly longer.

When using roll-offset-paper, the moisture content may need to be increased before use as it is important to ensure there is enough water to ensure a fast chemical reaction.

TECHNOMELT® PUR 3317 BR has a good adhesion to PVC and Acetate-films. Bonding of PP- and PE-films is only possible after a recent Corona pretreatment with a surface tension of >40 mN/m (old: dyn/cm).

Film properties

- white
- transparent
- hard elastic

Technical data

TECHNOMELT® PUR 3317 BR:

Viscosity, mPa.s	2,500 to 4,500
Brookfield Thermosel, 130°C	
Open time	medium

Direction for use

Preliminary statement

Prior to application it is necessary to read the **Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Processing

Depending on size and weight of the book the thickness of the adhesive film should be 0,3 – 0,6mm. For book blocks greater than 1 cm thick we recommend usage at the higher levels of this range.

Application

Application method

- roller
- nozzle

Recommended working temperature 115 -130 °C

Working temperature

In our experience the actual temperature on the roller and nozzle is often lower than the set temperature. To ensure the actual temperature is the same as the recommended one for the adhesive we suggest to regularly check with an external thermometer and adjust as required.

Processing of TECHNOMELT® PUR 3317 BR with bulk melter should be effective at the following temperatures

Premelting area, °C	80 to 90
Hose, °C	110 to 120
Glue applicator / roller, °C	120 to 130
Nozzle, °C	120
Spinner, °C	150

For the production of very thick books the temperature of the melting plate may increase by 10 to 50 °C and of the hose by 10 to 20 °C in order to secure a continuous and sufficient flow of premelt into the glue applicator. **Important:** Do not forget to reduce the temperatures back to the a.m. levels afterwards.

Only specially coated devices can be applied for premelting. When the machines are stopped for a longer period of time, the premelt and application temperatures should be reduced to a minimum. Excessive exposure to higher temperature leads to an increase of the viscosity.



Cleaning

We recommend to use our TECHNOMELT PUR CLEANER ME to clean the applicators and adhesive tanks. While working with the cleaning agent, please strictly observe the safety regulations. Bulk melters can be cleaned by means of reactive melt TECHNOMELT PUR CLEANER 2 (light blue). Hoses containing (partly) cured adhesive and upstream bulk melter can be cleaned with Purmelt Cleaner all-in-one (light red).

During use, please follow the safety instructions.

Handling information

Due to the variety of different materials available on the markets pre-tests should be carried out.

Storage

Rotate stock, using oldest material first. Keep containers upright and closed to prevent contamination. Do not mix with other adhesives. When stored in a dry and cool place in the original unopened containers shelf life is as follows.

Shelf life

Shelf-life (in unopened original packaging), months	12
Frost-sensitive	No

Classification

Please refer to the corresponding **Safety Data Sheet** for details on:

Hazardous Information

Transport Regulations

Safety Regulations

Additional information

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 2