

TECHNOMELT® PUR 4663 NA20

January 2026

Product description

TECHNOMELT® PUR 4663 NA20 provides the following product characteristics:

Technology	Polyurethane
Product type	Hotmelt

TECHNOMELT® PUR 4663 NA20 is a high performance, reactive, moisture curing hotmelt adhesive based on Polyurethane-Prepolymers. The adhesive is pressure sensitive and gives a special high initial strength instantly after joining the parts. Therefore, it is suitable for substrates with a very high reaction force. Additionally, it has a long open time so that joining is still possible after cooling. After moisture curing the product has duroplastic properties and a very high heat and cold resistance.

Application areas

- TECHNOMELT® PUR 4663 NA20 was especially designed for industrial flat lamination but may also be used for assembly application.
- The adhesive has a very broad adhesion spectrum and demonstrates also good flexibility.
- It can be used to bond wood, plastic, textiles, different films and foams and is also well suitable for bonding pretreated substrates.
- It is mainly developed for lamination where the ambient conditions are greater than 30°C.
- Provide high initial green strength for edge wrapping applications.

Technical data

TECHNOMELT® PUR 4663 NA20:

Color	opaque when molten, after cooling light ivory, crystalline in UV-light fluorescent
Odor	weak characteristic
Density, g/m ³	approx. 1.1
Solid content, %	100
Viscosity at 120°C, mPa.s (cP)	6500 - 10000
Equipment	Brookfield
Measuring system	Thermosel SP 27
Open time, s	~ 90 (depending on mode of application, layer thickness and the substrates)
Application temperature, °C	120 - 140

Direction for use

Preliminary statement

Prior to application it is necessary to read the **Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Pretreatment

- The bonding surfaces must be clean, dry and free of oil and grease.
- Substrate temperature should not fall below 20°C during application.
- Lower temperatures will lead to an early solidification of the adhesive and thus to a reduced open time, possibly the adhesive might even flake off.
- If necessary the substrates may be prewarmed, however, longer open times and thus extended cycle times will have to be taken into consideration at temperatures above 45°C.

Application

TECHNOMELT® PUR 4663 NA20 can be applied from heatable cartridge guns, from usual tank melting equipment and from drums or hobboscks, using heatable equipment. The material may be applied by nozzle, roller, foamable and sprayable systems. At longer rest periods melting and application temperatures should be decreased. Longer exposure to higher temperatures can lead to a viscosity increase.

Curing

TECHNOMELT® PUR 4663 NA20 cures exclusively by moisture and gains its final strength after 3 - 7 days but exhibits high handling strength after the physical process of setting.

Curing is a chemical reaction depending on the following parameters:

- humidity of the substrates (carrier and decor)
- humidity in the rooms for application and storage (assure possibility of humidity access; the adhesive will react extremely slowly with parts being wrapped in plastic foils!)
- permeability of the substrates to be bonded
- application weight/layer of the adhesive film

Cleaning:

If TECHNOMELT® PUR 4663 NA20 is not cured application equipment can be cleaned with Purmelt Cleaner 02 (See separate Technical Data Sheet.) Cured adhesive can only be removed mechanically.

Storage

Frost-sensitive	no
Recommended storage temperature, °C	5 - 25
Shelf-life (in unopened original packaging), months	6

Classification

Please refer to the corresponding **Safety Data Sheets** for details on:

Hazards identification

Transport information

Regulatory information

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1