

TEROSON® EP 5075 SB

September 2024

Product description

TEROSON® EP 5075 SB provides the following product characteristics:

Technology	Epoxy
Chemical type	Epoxy
Appearance (resin)	Pink
Appearance (hardener)	Amber
Appearance (mixed) – uncured	Pink
Appearance (mixed) –cured	Purple
Components	Two components – requires mixing
Viscosity	Low to medium
Mix ratio, (by volume) Resin : Hardener	2 : 1
Cure	Room temperature cure after mixing, accelerated cure at elevated temperature
Application	Bonding
Application temperature	10 to 35°C (50 to 95°F)
In service temperature	-40 to 90°C (-40 to 194°F)
Specific benefits	<ul style="list-style-type: none"> • High Impact resistance, high durability against fatigue and stress • Complies with high crash safety standard • High crash performance at extreme temperatures (both low and high) • Adheres to a wide range of materials (without primer) and dissimilar metals • Compatible with spot welding and riveting methods • Contains Glass beads (0.20mm) to provide uniform bond-line control • Color changing technology to indicate the degree of curing

TEROSON® EP 5075 SB is a solvent free, two-component, high strength impact resistant adhesive, based on toughened epoxy resin.

It is designed to meet with the upgraded OEM impact resistance specifications, which requires higher impact peel strength compared to the conventional Impact Resistant Structural Adhesives.

It has a high impact resistance at both high and low temperatures (-40°C to 80°C) which means, the adhesive provides high crash safety at a full temperature spectrum. The cured adhesive film is hard, but not brittle.

It is made for professionals to be mainly used in structural bonding of metals in car repair when crash behavior requirements are high.

Typical application areas are engine mounts, strut tower, radiator support, A & B pillars, aprons, core supports, roof frame, rocker panel, wheel arch, floors, and safety critical parts.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Resin

Specific gravity @ 23°C	1.14
Viscosity, mPa·s (cP):	75,000
Physica Rheometer @25°C	
Plate/plate Ø 40 mm, Shear rate: 20 s ⁻¹	

Hardener

Specific gravity @ 23°C	1.09
Viscosity, mPa·s (cP):	45,000
Physica Rheometer @25°C	
Plate/plate Ø 40 mm, Shear rate: 20 s ⁻¹	

TYPICAL CURING PERFORMANCE

Working time

Working time @23°C, minutes	60
ASTM D 2471	

Fixture time

Fixture time is defined as the time to develop a shear strength of 0.1 N/mm².

Fixture Time, @23°C, hours	6
----------------------------	---

Final cure time

Final Cure, @ 23°C, hours	48
Final cure, accelerated cure @ 60°C, hours	2
Final cure, accelerated cure @ 80°C, minutes	45

TYPICAL PERFORMANCE OF CURED MATERIAL**Physical properties**

Elongation, at break, ISO 527, %		5
E-Modulus, ISO 527, cured for 7 days @23°C	N/mm ² (psi)	1,600 (230,000)
Tensile Strength, at break, ISO 527	N/mm ² (psi)	26 (3,800)

Cured for 7 days @ 23°C
Impact Peel, ISO 11343;
CRS, sanded w/ 80 grit

Tested @ 23°C	N/mm (lb/in)	27 (150)
Tested @ 80°C	N/mm (lb/in)	20 (114)
Tested @ -40°C	N/mm (lb/in)	19 (108)

Adhesive properties

Cured for 7 days @ 23°C Lap Shear Strength, DIN 1465: CRS, sanded w/ 80 grit		
Tested @ 23°C	N/mm ² (psi)	30 (4,400)
Tested @ -40°C	N/mm ² (psi)	46 (6,700)

Cured for 30 mins @60°C, Cured for 7
days @23°C
Impact Peel, ISO 11343;
CRS, sanded w/ 80 grit

Tested @ 23°C	N/mm (lb/in)	26 (148)
Tested @ 80°C	N/mm (lb/in)	31 (180)
Tested @ -40°C	N/mm (lb/in)	31 (180)

Cured for 30 mins @60°C, Cured for 7 days
@23°C

Lap Shear Strength, DIN 1465: CRS, sanded w/ 80 grit		
Tested @ 23°C	N/mm ² (psi)	32 (4,600)
Tested @ -40°C	N/mm ² (psi)	46 (6,700)

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Direction for use**Pretreatment:**

- Bonding surfaces must be free of oil, grease, dust, or any other contaminant. Pretreat bonding surfaces with alcohol based cleaner and a lint-free cloth.
- Remove old adhesive from existing body parts to make sure they are back to bare metal and free of any contamination.
- Both bonding surfaces must be cleaned again to remove grinding dust. Pretreat bonding surfaces with alcohol based cleaner. Allow the prepared surfaces to dry for approx. TEROSON® VR 10 ..

Cured for 7 days @ 23°C

"T" Peel Strength, ISO 11339: CRS, sanded w/ 80 grit		
Tested @ 23°C	N/mm (lb/in)	8 (46)

Cured for 30 mins @60°C, Cured for 7 days
@23°C

"T" Peel Strength, ISO 11339: CRS, sanded w/ 80 grit		
Tested @ 23°C	N/mm (lb/in)	9 (51)



Curing

1. Cure speed may vary based on adhesive and substrate temperature.
2. During the curing phase, adhesive color will start to change from pink to dark purple. The change in the color is an indication of curing process.
3. Please avoid movement or stress until the product is fully cured.

Application:

1. Unscrew the coupling ring and remove the cap from TEROSON® EP 5075 SB Panel Bonder cartridge. Before attaching the static mixer to the cartridge, squeeze out a small amount of material until both adhesive components run equally. This is necessary to achieve a good mix of the two components.
2. Attach the static mixer and fix it with the coupling ring. Insert the cartridge into the application dispenser. Only use dispensers that are equipped with a piston rod.
3. When mixed, TEROSON® EP 5075 SB is pink color. Discard first 5 cm of adhesive.
4. Apply and spread TEROSON® EP 5075 SB with a spreader or brush. All bare metal areas should be covered with adhesive for corrosion protection. TEROSON® EP 5075 SB can be used on steel and aluminum panels and as part of the preparation.
5. It may be necessary to change the static mixer if no material has been passed through it in over 30 minutes.
6. Join and fix components within the 60 minutes processing time. The processing time depends on the temperature. If spot welding is required, it must be carried out during this initial period. Do not subject bonded parts to stress before final cure. In order to avoid the bonded parts being displaced, it is recommended that they should always be fixed during the process of curing.
7. To ensure high crash safety performance, the assembly bonded shall be designed so that the bonded surface or seams are only subjected to tensile or shear forces, but not to peel forces. It is recommended that bonding should be done with single overlaps.
8. After use, leave the static mixing nozzle in place to seal the cartridge.

Cleaning:

1. It is important to clean up excess adhesive from the work area and application equipment before it hardens.
2. Remove excess adhesive immediately with spatula or cloth and TEROSON® VR 10. Cured adhesive can only be removed mechanically.

Painting:

1. TEROSON® EP 5075 SB can be painted when initial bond strength has been reached.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 15°C to 35°C (59°F to 77°F).

Under certain conditions, the product is frost sensitive. It may crystallize but it is reversible >40°C (104°F).

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Product Specification

The technical data contained herein are intended as reference only and are not considered specifications for the product.

Product specifications are located on the Certificate of Analysis or please contact Henkel representative.

Approval and Certificate

Please contact Henkel representative for related approval or certificate of this product.

Data Ranges

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23°C / 50% RH = 23±2°C / 50±5% RH

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1