

TEROSON PU 1510

February 2016

PRODUCT DESCRIPTION

Technology	1c-Polyurethane Encapsulated Isocyanate
Product Type	Adhesive
Additional Function	Solvent free Thermosetting

TEROSON PU 1510 is a one-component, thermosetting adhesive based on encapsulated isocyanate. Curing requires temperatures above 90 °C inside the adhesive, at lower temperatures it is incomplete or will not happen at all. Already after 30 seconds the products is solidified and achieves between 60 and 80 % of its final strength, provided that the heat acts throughout the whole adhesive sheet.

APPLICATION AREAS

TEROSON PU 1510 is used for bonding of primed respectively painted metal parts, i.e. modules in the automotive or commercial vehicle industry. Also high-strength plastics, as for instance fiber reinforced composites (GFRP, CFRP etc.) are possible substrates. It is recommended to test the suitability in advance.

TECHNICAL DATA (Typical Test Results)

Colour:	black
Density:	approx. 1.5 g/cm ³
Solids:	approx. 99 %
Consistency:	paste
Rheological characteristics	
Equipment:	Physica MCR 300
Viscosity:	100 to 300 Pa.s
Yield Point (Casson):	300 to 800 Pa
Tensile strength (DIN 53504)	> 11 MPa
Elongation at break (DIN 53504)	> 110 %
Lap Shear Strength (30min. 100°C)	approx. 10.5 MPa thickness 1mm
Shore-A-hardness: (30 min. 100°C)	approx. 90
Curing temperatures:	Curing possible between 90 and 170 °C
Application temperature:	18 °C to 35 °C at lower storage temperatures make sure that the containers are brought to application temperature in time, prior to application
Open Time: (DIN 50014 standard climate 23°C, 50% r.h.)	3 h
In service temperature range:	-40 to 100 °C

Temperature resistance:

Short exposure (up to 1h) 170 °C

PRELIMINARY STATEMENT

Prior to application it is necessary to read the Safety Data Sheet for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

DIRECTIONS OF USE

Pretreatment

The parts to be bonded must be free from oil, grease, moisture, dirt and release agents. From the Henkel portfolio for example TEROSON PU 8550 or TEROSON VR 20 can be used as cleaners. In the case of plastics a flame pre-treatment like plasma or corona can be necessary to ensure good adhesion of TEROSON PU 1510 to the substrate. Occasionally usage of a primer is also an option.

APPLICATION

Packaging and inliner shall be opened directly before use. If the material cannot be consumed rapidly, the following measures have to be regarded:

- The packaging must be covered tightly by the follower plate.
- In case of longer breaks (more than 60 minutes downtime without material consumption) a complete pressure relief and, on heated parts of the system, a temperature switch-off has to be carried out.
- The recommended storage temperature (10°C to 30°C) has to be maintained.

In addition, after a longer stoppage (i.e. after weekends) the equipment must be rinsed sufficiently with fresh material.

In consideration of these measures a package can remain under the equipment up to maximum 2 months after opening, but at most until end of its shelf life.

TEROSON PU 1510 is applied with piston type pumps with a compression ratio of minimum 48:1, equipped with follower plate and over-stroke alert. Due to the high reactivity of the product, not more than 6 strokes / minute shall be allowed. Hydraulically or electrically driven piston dosing systems are recommended for the dosing. In case of alternative dosing units preliminary suitability tests have to be conducted.

All parts of the equipment which can get in contact with TEROSON PU 1510 must be made of stainless steel grade 1.4301 or better. Alternatively inert coatings, as for instance PTFE, can be used.

TEROSON PU 1510

February 2016

Curing

Besides hot air (convection oven) also electromagnetic radiation (i.e. infrared radiation, microwaves) or magnetic fields for heating up the substrates (induction devices) can serve as energy source.

Cleaning

Freshly applied and uncured material should be removed with a dry cloth and then cleaned off with a suitable solvent. Cured adhesive can only be removed mechanically.

STORAGE

Frost sensitive	no
Recommended storage temperature	10 to 30 °C
Shelf life	9 months

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to

determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Henkel AG & Co. KGaA

D-40191 Düsseldorf, Germany
Phone: +49-211-797-0
www.henkel.com

Henkel Central Eastern Europe GmbH

A-1030 Wien, Austria
Phone: +43-1711-040
www.henkel.com

Henkel & Cie AG

CH-4133 Pratteln, Switzerland
Phone: +41-61-825-7000
www.henkel.com

