

TEROSON VR 625

September 2016

PRODUCT DESCRIPTION

TEROSON VR 625 provides the following characteristics:

Technology	Rust Converter Film-Forming, Solvent-Based Rust-Converting Aerosol
Base	Synthetic Resin
Additional Information	free from Phosphoric Acid

TEROSON VR 625 is used to treat areas of rust of all kinds. Organic agents convert the rust (iron oxides) into a stable complex compound; during this process, the clear, slightly brownish liquid changes through dark blue into brown-black colour. The synthetic resin forms a paint-like protective film when dry. This good sandable protective film with excellent adhesion remains on the metal and may be used as a primer. No additional priming is required.

APPLICATION AREAS

TEROSON VR 625 is suitable for use on all ferrous substrates, such as industrial applications and automotive maintenance / repair. TEROSON VR 625 is not suitable for parts subject to high temperatures such as exhaust systems, stove chimney pipes etc.

TECHNICAL DATA

(Typical Test Results)

Colour	clear, slightly brownish liquid
Odour	of solvents
Density	approx. 0.91 g/cm ³
Solids	approx. 27 %
pH value	3
Application thickness	0.1 to 0.2 mm per coat
Coverage	approx. 0.25 l/m ²
Drying time	
Touch dry	approx 20 min.
Fully dry	16 hours
Application temperature	8 to 25 °C
In service temperature range	-30 to 80 °C
short exposure (up to 1h)	100 °C

PRELIMINARY STATEMENT

Prior to application it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

Pretreatment

The surfaces to be coated with TEROSON VR 625 have to be clean, dry and free of rust, oil, grease, dust and other contamination. Areas not to be coated should be properly covered. Bare sheet steel must always be coated with wash primer prior to coating with TEROSON VR 625.

Application

TEROSON VR 625 is applied by spraying out from aerosol can. Shake can well before use. Keep spray distance of 20-30 cm to the spray area to be treated.

Spray 2 or 3 thin layers "wet in wet" without sagging. Let the layer convert and dry. In case it will be covered by another coating, please sand the layer to improve the adhesion of this next layer.

Practice

The product is touch dry after approx. 20 minutes.

Overnight drying is required for full drying.

The drying time is dependent from temperature and layer thickness.

Higher temperatures will increase the cure speed, cold weather and humid environment could prolong the drying time.

The dried coating may be overpainted with most of the industrial and repair paints (after ca. 16 hours).

Application tools should be cleaned with solvents immediately after completion of work.

Any product which has already formed a film will have to be removed mechanically.

STORAGE

Frost sensitive	yes
Recommended storage temperature	10 to 25 °C
Shelf life	24 months

Disclaimer

TEROSON VR 625

September 2016

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Henkel AG & Co. KGaA

D-40191 Düsseldorf, Germany

Phone: +49-211-797-0

www.henkel.com

Henkel Central Eastern Europe GmbH

A-1030 Wien, Austria

Phone: +43-1711-040

www.henkel.com

Henkel & Cie AG

CH-4133 Pratteln, Switzerland

Phone: +41-61-825-7000

www.henkel.com

