



# Technical Data Sheet



Technical Data Sheet  
Ref: UC3100  
Issued: 22.11.2023  
Number of pages: 3

## UniBond No More Nails Invisible 41g Tube



### CHARACTERISTICS

- INSTANT TACK® Solvent-free dispersion formula
- No need to support joints with mechanical fixings
- 70 kg/m<sup>2</sup> initial tack
- High adhesion properties
- Over paintable once dry
- High adhesion especially wood to wood
- Gap filling up to 10 mm.
- Minimum application temperature +10°C
- Low odour
- Transparent after drying
- Interior use

### APPLICATION FIELD

UniBond No More Nails Invisible is suitable for the following surfaces: plaster (indoor), concrete, plaster board, gypsum boards, wood materials (e.g. chip boards) and polyurethane rigid-foams.

Fixing:

- Skirting boards
- Coving
- Polystyrene mouldings
- Window ledges
- Coat hooks and many other internal bonding applications

### INSTRUCTIONS FOR USE


#### Pretreatment

Ensure surfaces to be bonded are clean, dry and free from contaminants likely to impair adhesion. Dries by water evaporation, therefore one of the surfaces being bonded must be porous. Prime very porous surfaces.



## Application

Apply adhesive onto one of the surfaces: 1) In spots in order to smooth uneven surfaces, 2) in wave-like form for higher initial tack with wide surfaces or 3) in straight strands for smaller surfaces.



Application of the adhesive

## Bonding of panels, plastic decoration details, acoustic panels etc.:

Place panel 1-2 cm off the area to be bonded, then slide into correct position and press firmly with a twisting action. Heavy or distorted items may need additional fixings or support whilst drying.

## TECHNICAL DATA

Composition	Dispersion
Density	approx. 1,03 g/cm <sup>3</sup>
Heat resistance	-20°C up to +70°C
Open time	Approx. 15 min
Application temperature	+10°C up to +40°C
Initial tack	15 to 20 g/cm <sup>2</sup>
Final strength (DIN EN 205)	5 to 6 N/mm <sup>2</sup>
Shelf Life	18 months From date of production if stored in unopened original tubes, in dry conditions and protected from direct sunlight at temperatures between +5°C and 25°C
Setting time	24- 48 hours
Consumption	Approx. 7 m using a 5mm bead, or approx. 300g/m <sup>2</sup>

## LIMITATIONS

Only for interior use in dry service conditions  
Not suitable for areas of constant immersion or permanent damp  
Dries by water evaporation, so one of the surfaces to be bonded must be porous (absorbent)  
Very heavy items may require support whilst drying or additional fixings  
Not suitable for fixing mirrors

## Cleaning



Immediately remove any adhesive residue with a damp cloth. Cured material can only be removed mechanically.

**Storage**

Store in cool dry conditions, protected from frost  
Replace cap after use.

**Packaging**

41g PE -tube

**HEALTH AND SAFETY**

Before using the product please see related Material Safety Data Sheet that is available to download from [mysds.henkel.com](http://mysds.henkel.com).

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**Henkel Limited**

Wood Lane End, Hemel Hempstead, Hertfordshire, HP2 4RQ  
Phone: +44 (0) 1606 593 933  
Internet: [www.henkel.co.uk](http://www.henkel.co.uk)  
e.mail: [technical.services@henkel.co.uk](mailto:technical.services@henkel.co.uk)